

BLAKES THINNERS

BLAKES PAINT is produced and supplied in such a way that thinning is normally not necessary provided the paint is properly mixed/stirred.

However, if the paint is to be applied in a low film thickness (for instance as a "sealer coat") or if the paint has become too thick, e.g. in hot or cold weather, the BLAKES THINNER(s) indicated on the product data sheet may be added to obtain a consistency most suitable for application. As a general rule, thinning should be kept at a minimum as the quality of the paint work will suffer from too liberal thinning.

However, if application is to take place at high temperatures (air and/or steel), thinning beyond the limits mentioned on the data sheets could be necessary in order to avoid dry-spray and poor film formation.

BLAKES THINNERS are blended to give the best results with regard to brush ability, spray properties, etc. In some cases ordinary solvents may substitute. As such products are beyond our control, we disclaim any responsibility for the results. In each case the respective product data sheet and - when available - the APPLICATION INSTRUCTIONS should be consulted. As regards the use of THINNERS for cleaning of tools, see REMARKS overleaf.

BLAKES THINNER NO.	FLASH POINT (Setaflash closed cup)	EXAMPLES OF GENERAL USE
No 1 (08231)	32°C	BLAKES BILGE & LOCKER PAINT BLAKES YACHT ENAMEL BLAKES PRIMER UNDERCOAT BLAKES FAVOURITE VARNISH BLAKES DURA-GLOSS VARNISH BLAKES DURA-SATIN VARNISH BLAKES CLASSIC VARNISH BLAKES BRILLIANT ENAMEL
No 2 (08711)	47°C	BLAKES POLYGLOSS (BRUSH) BLAKES DIAMOND VARNISH BLAKES WOODSEAL
No 3 (08081)	25°C	BLAKES UNDERWATER PRIMER BLAKES BROADS ANTIFOULING BLAKES DECK PAINT BLAKES HARD RACING ANTIFOULING BLAKES KEEL PRIME BLAKES WATERLINE ANTIFOULING BLAKES TIGER XTRA BLAKES CRUISING PERFORMER BLAKES OCEAN PERFORMER
No 5 (08451)	26°C	BLAKES EPOXY PRIMER UNDERCOAT BLAKES GELPROTECT SFE200
No 6 (08511)	3°C	BLAKES POLYGLOSS (SPRAY)

2. BLAKES THINNERS

REMARKS:	Tools can usually be cleaned with the THINNER prescribed for the product or as described in the product data sheet.		
Note:	The information given in the Technical Data Sheet is intended for commercial use.		
SAFETY:	Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult BLAKES Material Safety Data Sheets and follow all local or national safety regulations. Avoid inhalation, avoid contact with skin and eyes, and do not swallow. Take precautions against possible risks of fire or explosions as well as protection of the environment. Apply only in well ventilated areas.		
ISSUED:	JUNE 2004 BLAKES PAINTS	0808000000CO004 0823000000CO005 0845000000CO009 0851000000CO002 0871000000CO002	

This Product Data Sheet supersedes those previously issued. For definition and scope, see explanatory notes to applicable Product Data Sheets.

Data, specifications, directions and recommendations given in this data sheet represent only test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use of the Products herein must be determined exclusively by the Buyer and/or User. The Products are supplied and all technical assistance is given subject to BLAKES PAINTS GENERAL CONDITIONS OF SALES, DELIVERY AND SERVICE, unless otherwise expressly agreed in writing. The Manufacturer and Seller disclaim, and Buyer and/or User waive all claims involving, any liability, including but not limited to negligence, except as expressed in said GENERAL CONDITIONS for all results, injury or direct or consequential losses or damages arising from the use of the Products as recommended above, on the overleaf or otherwise.

Product data are subject to change without notice and become void five years from the date of issue.