

## PRODUCT DESCRIPTION

Suitable for priming GRP below the waterline. Avoids the need for extensive sanding of GRP.

## PRODUCT INFORMATION

Colour	YPA142-Grey
Finish	Matt
Specific Gravity	1.7
Volume Solids	45%
Typical Shelf Life	2 yrs
Unit Size	2.5 Lt

## DRYING/OVERCOATING INFORMATION

	Drying			
	5°C	15°C	23°C	35°C
Immersion	4days	3days	3days	2days

Overcoated By	Overcoating							
	Substrate Temperature							
	5°C		15°C		23°C		35°C	
	Min	Max	Min	Max	Min	Max	Min	Max
B.F.A.	8hrs	1wks	4hrs	1wks	2hrs	1wks	2hrs	1wks
Boatgard	8hrs	1wks	4hrs	1wks	2hrs	1wks	2hrs	1wks
Cruiser Premium	8hrs	1wks	4hrs	1wks	2hrs	1wks	2hrs	1wks
Cruiser UNO	8hrs	1wks	4hrs	1wks	2hrs	1wks	2hrs	1wks
Interspeed Kopervrij	8hrs	1wks	4hrs	1wks	2hrs	1wks	2hrs	1wks
Interspeed Ultra	8hrs	1wks	4hrs	1wks	2hrs	1wks	2hrs	1wks
Micron Extra	8hrs	1wks	4hrs	1wks	2hrs	1wks	2hrs	1wks
Micron Kopervrij	8hrs	1wks	4hrs	1wks	2hrs	1wks	2hrs	1wks
New Waterways	8hrs	1wks	4hrs	1wks	2hrs	1wks	2hrs	1wks
Trilux	8hrs	1wks	4hrs	1wks	2hrs	1wks	2hrs	1wks
Trilux 33	8hrs	1wks	4hrs	1wks	2hrs	1wks	2hrs	1wks
Uni-Pro	8hrs	1wks	4hrs	1wks	2hrs	1wks	2hrs	1wks
VC Offshore	8hrs	1wks	4hrs	1wks	2hrs	1wks	2hrs	1wks
Waterways	8hrs	1wks	4hrs	1wks	2hrs	1wks	2hrs	1wks

## APPLICATION AND USE

**Preparation** **BARE GRP:** Clean and degrease the surface with Fibreglass Surface Prep. Apply the Fibreglass Surface Prep using either a cloth or sponge with a polishing action. The Fibreglass Surface Prep may then be removed with a regularly rinsed cloth or by pressure washing. If the interval between degreasing and applying Fibreglass No Sand Primer exceeds 4 hours, clean the surface with fresh water and allow to dry.

**Method** Apply 1 coat only.

**Hints** **Mixing** Stir thoroughly before use.

**Thinning** Do not thin.

**Cleaner** YTA085 Thinners No.3

**Ventilation and Humidity Control** Should it rain during or immediately after application, the coating must be exposed to dry conditions for at least 24 hours before overcoating. In cold conditions, <10°C, 48 hours is recommended.

**Other** Unsuitable for application between tides.

**Some Important Points** Protect from frost. Do not use under 2 component solvent based products. Do not use in wet or

humid conditions. Product temperature should be minimum 5°C/40°F and maximum 35°C/95°F. Ambient temperature should be minimum 5°C/40°F and maximum 35°C/95°F. Substrate temperature should be minimum 5°C/40°F and maximum 35°C/95°F.

<b>Compatibility/Substrates</b>	GRP only.
<b>Number of Coats</b>	1
<b>Coverage</b>	(Theoretical) - 9.00 (m <sup>2</sup> /lt)
<b>Recommended DFT</b>	45 microns dry
<b>Recommended WFT</b>	100 microns wet
<b>Application Methods</b>	Brush, Roller

## TRANSPORTATION, STORAGE AND SAFETY INFORMATION

<b>Storage</b>	<p><b>GENERAL INFORMATION:</b> Exposure to air and extremes of temperature should be avoided. For the full shelf life of Fibreglass No Sand Primer to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/40°F and 35°C/95°F. Keep out of direct sunlight.</p> <p><b>TRANSPORTATION:</b> Fibreglass No Sand Primer should be kept in securely closed containers during transport and storage.</p>
<b>Safety</b>	<p><b>GENERAL:</b> Read the label safety section for Health and Safety Information, also available from our Technical Help Line.</p> <p><b>DISPOSAL:</b> Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.</p> <p>Remainders of Fibreglass No Sand Primer cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.</p>

**IMPORTANT NOTES** *The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal or injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.*

**X** and International are registered trademarks of Akzo Nobel.

## Regional Addresses

**Head Office**  
International Paint Ltd  
P O Box 20980  
Oriental House  
16 Connaught Place  
London W2 2ZB  
United Kingdom  
tel: +44 (0) 171 479 6000  
fax: +44 (0) 171 479 6500

**European Region**  
International Paint Ltd  
Stoneygate Lane  
Felling, Gateshead  
Tyne & Wear NE10 0JY  
United Kingdom  
tel: +44 (0) 191 469 6111  
fax: +44 (0) 191 438 3977

**Asia Region**  
International Paint Singapore  
(Pte) Ltd  
449 Tagore Industrial Avenue  
01-03 Hong Joo Industrial  
Building  
Singapore 787820  
tel: +65 6453 1981  
fax: +65 6453 1778

**Australasia Region**  
International Paint  
115 Hyde Road  
Yeronga, Brisbane  
Queensland 4104  
Australia  
tel: +61 (0) 7 3892 8866  
fax: +61 (0) 7 3892 4287

**North America Region**  
International Paint LLC  
2270 Morris Avenue  
Union  
New Jersey 07083  
USA  
tel: +1 (0) 908 686 1300  
fax: +1 (0) 908 686 8545

**South America Region**  
International Paint  
Rod Rap tavares, KM 18.5  
Predio Administrativo 11  
Butanta CEP 05577-300  
Sao Paulo, Brazil  
tel: +55 (0) 11 3789 2000  
fax: +55 (0) 11 3789 2200



Ref: 05000141  
Issue Date: 12-Mar-2005  
Supersedes: 7-Apr-2003