

PRODUCT DESCRIPTION

Interfill 830 is the best choice for profiling above and below the waterline on Steel, Aluminium and Composite hulls. The special 2-component light grey epoxy formulation can fill up to a thickness of 1 inch in one coat without the risk of sagging/slumping.

- * Low density composition
- * High strength and impact resistance
- * Easy sanding
- * Waterproof

When sanded, the surface of the Interfill 830 is smooth enough to be directly overcoated with Interprime 820 high build epoxy primer. Interprime 850 or Interprime 880 may also be used. Interfill 830 is particularly suitable for application over large areas.

PRODUCT INFORMATION

Colour	YAA867-Grey
Finish	Matt
Specific Gravity	0.75
Volume Solids	100%
Mix Ratio	1:1 by volume (as supplied) Mix ratio by weight: 1.15:1 YAA867: YAA868, Converter/Curing Agent - YAA868
Typical Shelf Life	2 yrs
VOC (As Supplied)	1 g/ltr
Unit Size	5 Lt 20 Lt

DRYING/OVERCOATING INFORMATION

	Drying			
	10°C	15°C	23°C	35°C
Sandable	48hrs	28hrs	19hrs	13hrs
Pot Life	75mins	55mins	45mins	20mins

Overcoated By	Overcoating							
	Substrate Temperature							
	10°C		15°C		23°C		35°C	
	Min	Max	Min	Max	Min	Max	Min	Max
Interfill 835	5days	-	3days	-	2days	-	1days	-
Interprime 820	5days	-	3days	-	2days	-	1days	-
Interprime 880	5days	-	3days	-	2days	-	1days	-
Interprotect (Professional)	5days	-	3days	-	2days	-	1days	-

Note: Once the sandable time has been exceeded, all fillers should be sanded before overcoating to promote good adhesion. A sanded filler may be left for a period up to 3 months before being overcoated with further epoxy filler or with Interprime 8-series. After 3 months the filler must then be re-sanded before overcoating.

APPLICATION AND USE

Preparation

All substrates must be primed, clean and dry.

PREVIOUSLY PAINTED SURFACES:

In Good Condition: Wash down with Yacht Line Super Cleaner, rinse with fresh water and allow to dry. Sand with 80-180 grade (grit) paper.

In Poor Condition: Remove all previous coatings and prime the substrate.

STEEL/ALUMINIUM: Prime with Intergard 269 or Interprime 820.

BARE WOOD: Prime stable constructions only, with Interprime 820.

GRP: For osmosis treatment follow the Gelshield specification ensuring the Interfill 830 is only used during STAGE 2.

BARE GRP/COMPOSITE: Sand with 80-180 grade (grit) paper.

If left for longer than 24 hours, two component epoxy primers and fillers will need sanding with 80-180 grade paper to ensure a good physical key.:

Method	Mix the two components thoroughly to an even colour. Remove any dust from the surface. Apply firmly in a spreading action. When hardened, sand smooth with 80-180 grade wet or dry paper. Interfill 830 may be overcoated with itself or with Interfill 833 as soon as it is cured enough not to be lifted during the screeding process.
Hints	Thinner GTA220 for equipment cleaning only. Thinning Do not thin. Ventilation and Humidity Control Avoid conditions of low temperatures coupled with high humidity as this can result in the formation of a surface by-product which will need to be removed by detergent wash followed by fresh water rinse, or by sanding, prior to the application of any subsequent layers. Other Spread mix out on a board to avoid excess heat build up and to keep the working life as long as possible. When fairing a hull, two or three 'cross coats' of Interfill 830 will ensure the desired shape is obtained. Where large areas have been faired, sand with a longboard to allow for the curvature of the hull.
Some Important Points	Do not use unless mixed thoroughly with the curing agent at specified ratio. Do not apply more than recommended WFT at any one time. Do not use below 10°C/50°F. Do not thin. Do not wipe down cured filler with thinners/solvents. Substrate temperature should be minimum 10°C and maximum 35°C. Product temperature should be minimum 10°C and maximum 35°C. Ambient temperature should be minimum 10°C and maximum 35°C.
Compatibility/Substrates	Do not use on traditional wood constructions where the wood will expand and contract through changes in the moisture content. Interfill 830 should be applied over cured epoxy primers or fillers or onto cured GRP/Composite. Interfill 830 may be overcoated with Interfill 833, Interprime 820, Interprime 850, Interprime 880 or Interfill 835 (YAA855/YAA856). Gelshield or Gelshield 200 may be used over Interfill 830 within the osmosis schemes.
Number of Coats	As required
Coverage	(Theoretical) - 0.20 (m ² /lt) @ 5000 micron (200 mil) WFT.
Recommended DFT	20000 microns dry By Trowel or Batten.
Recommended WFT	20000 microns wet By Trowel or Batten.
Application Methods	Trowel, Batten

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage	GENERAL INFORMATION: Exposure to air and extremes of temperature should be avoided. For the full shelf life of Interfill 830 to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/40°F and 35°C/95°F. Keep out of direct sunlight. TRANSPORTATION: Interfill 830 should be kept in securely closed containers during transport and storage.
Safety	GENERAL: Read the label safety section for Health and Safety Information, also available from our Technical Help Line. DISPOSAL: Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal. Remainders of Interfill 830 cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.
IMPORTANT NOTES	<i>The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal or injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.</i> X and International are registered trademarks of Akzo Nobel.

Regional Addresses

Head Office International Paint Ltd P O Box 20980 Oriental House 16 Connaught Place London W2 2ZB United Kingdom tel: +44 (0) 171 479 6000 fax: +44 (0) 171 479 6500	European Region International Paint Ltd Stoneygate Lane Felling, Gateshead Tyne & Wear NE10 0JY United Kingdom tel: +44 (0) 191 469 6111 fax: +44 (0) 191 438 3977	Asia Region International Paint Singapore (Pte) Ltd 449 Tagore Industrial Avenue 01-03 Hong Joo Industrial Building Singapore 787820 tel: +65 6453 1981 fax: +65 6453 1778	Australasia Region International Paint 115 Hyde Road Yeronga, Brisbane Queensland 4104 Australia tel: +61 (0) 7 3892 8866 fax: +61 (0) 7 3892 4287	North America Region International Paint Inc 2270 Morris Avenue Union New Jersey 07083 USA tel: +1 (0) 908 686 1300 fax: +1 (0) 908 686 8545	South America Region International Paint Rod Rap tavares, KM 18.5 Predio Administrativo 11 Butanta CEP 05577-300 Sao Paulo, Brazil tel: +55 (0) 11 3789 2000 fax: +55 (0) 11 3789 2200
---	--	---	--	--	--