

PRODUCT DESCRIPTION

Intertox is a clear, penetrating wood preservative for combating rot and fungal staining. One- and two-pack paints may be applied over Intertox for longer life.

PRODUCT INFORMATION

Colour	YMA117-Clear
Specific Gravity	0.84
Volume Solids	4%
Typical Shelf Life	2 yrs
Unit Size	1 Lt

DRYING/OVERCOATING INFORMATION

	Drying							
	5°C		15°C		23°C		35°C	
Touch Dry [ISO]	2hrs		1hrs		30mins		30mins	

Overcoated By	Overcoating							
	Substrate Temperature							
	5°C		15°C		23°C		35°C	
	Min	Max	Min	Max	Min	Max	Min	Max
Goldspar	4hrs	ext	2hrs	ext	1hrs	ext	30mins	ext
Goldspar Satin	4hrs	ext	2hrs	ext	1hrs	ext	30mins	ext
Interprotect	4hrs	ext	2hrs	ext	1hrs	ext	30mins	ext
Interstain	4hrs	ext	2hrs	ext	1hrs	ext	30mins	ext
Intertox	4hrs	ext	2hrs	ext	1hrs	ext	30mins	ext
Original	4hrs	ext	2hrs	ext	1hrs	ext	30mins	ext
Perfection Varnish	4hrs	ext	2hrs	ext	1hrs	ext	30mins	ext
Perfection Varnish for Teak	4hrs	ext	2hrs	ext	1hrs	ext	30mins	ext
Primocon	4hrs	ext	2hrs	ext	1hrs	ext	30mins	ext
Schooner	4hrs	ext	2hrs	ext	1hrs	ext	30mins	ext
Yacht Primer	4hrs	ext	2hrs	ext	1hrs	ext	30mins	ext

Note: Most International paints, varnishes and Interstain are compatible with Intertox and can be applied using the same overcoating times quoted for self overcoating.

APPLICATION AND USE

Preparation	BARE WOOD: Sand smooth with 80-180 grade paper and then 280 grade paper. Remove sanding dust by brushing, dusting and wiping. If wiping with solvent then allow to dry completely before applying the first coat.
Method	Apply liberally by brush paying particular attention to joints, screwholes and the end grain.
Hints	Thinner YTA800 Thinners No.1 Cleaner YTA800 Thinners No.1
Some Important Points	Product temperature should be minimum 5°C/40°F and maximum 35°C/95°F. Ambient temperature should be minimum 5°C/40°F and maximum 35°C/95°F. Substrate temperature should be minimum 5°C/40°F and maximum 35°C/95°F.
Compatibility/Substrates	Only use on bare wood. Not compatible with Teak, Iroko and other oily wood types. International's paints, varnishes and Interstain are compatible with Intertox. Do not use in conjunction with UCP. When used on immersed surfaces, Intertox must be overcoated with a suitable International paint.
Number of Coats	2-4

Coverage (Theoretical) - 10.00 (m²/lt) 8-12 m²/lt depending on porosity of wood.

Recommended DFT

Application Methods Brush

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage **GENERAL INFORMATION:**
Exposure to air and extremes of temperature should be avoided. For the full shelf life of Intertox to be realised ensure that between use the container is firmly closed and the temperature is between 5° C/40°F and 35°C/95°F. Keep out of direct sunlight.

TRANSPORTATION:
Intertox should be kept in securely closed containers during transport and storage.

Safety **GENERAL:** Contains biocides. Read the label safety section for Health and Safety Information, also available from our Technical Help Line.
DISPOSAL: Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.
Remainders of Intertox cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.

IMPORTANT NOTES *The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal or injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.*
X and International are registered trademarks of Akzo Nobel.

Regional Addresses

<u>Head Office</u> International Paint Ltd P O Box 20980 Oriol House 16 Connaught Place London W2 2ZB United Kingdom tel: +44 (0) 171 479 6000 fax: +44 (0) 171 479 6500	<u>European Region</u> International Paint Ltd Stoneygate Lane Felling, Gateshead Tyne & Wear NE10 0JY United Kingdom tel: +44 (0) 191 469 6111 fax: +44 (0) 191 438 3977	<u>Asia Region</u> International Paint Singapore (Pte) Ltd 449 Tagore Industrial Avenue 01-03 Hong Joo Industrial Building Singapore 787820 tel: +65 6453 1981 fax: +65 6453 1778	<u>Australasia Region</u> International Paint 115 Hyde Road Yeronga, Brisbane Queensland 4104 Australia tel: +61 (0) 7 3892 8866 fax: +61 (0) 7 3892 4287	<u>North America Region</u> International Paint Inc 2270 Morris Avenue Union New Jersey 07083 USA tel: +1 (0) 908 686 1300 fax: +1 (0) 908 686 8545	<u>South America Region</u> International Paint Rod Rap tavares, KM 18.5 Predio Administrativo 11 Butanta CEP 05577-300 Sao Paulo, Brazil tel: +55 (0) 11 3789 2000 fax: +55 (0) 11 3789 2200
--	--	---	--	--	--



Ref: 05000097
Issue Date: 4-Sep-2004
Supersedes: 1-Mar-2003