

## PRODUCT DESCRIPTION

Superyacht 900 Antifouling has been developed to provide long term protection for large yachts. Its fast polishing copolymer formulation is suitable for use on both sail and motor yachts and is strong enough to cope with high fouling conditions.

- \* Available in a range of colours
- \* Organotin copolymer formulation for premium performance
- \* Up to two years service life from two coats

## PRODUCT INFORMATION

<b>Colour</b>	YBA409-Off White, YBA419-Blue, YBA449-Red, YBA499-Black
<b>Finish</b>	Matt
<b>Specific Gravity</b>	1.6
<b>Volume Solids</b>	49%
<b>Typical Shelf Life</b>	2 yrs
<b>Unit Size</b>	20 Lt

## DRYING/OVERCOATING INFORMATION

### Drying

	5°C	15°C	23°C	35°C
Touch Dry [ISO]	6hrs	5hrs	4hrs	2hrs
Immersion	24hrs	18hrs	12hrs	12hrs

**Note:** Maximum immersion time is 4 months.

### Overcoating Substrate Temperature

	5°C		15°C		23°C		35°C	
	Min	Max	Min	Max	Min	Max	Min	Max
Overcoated By								
Superyacht 900 Antifouling	12hrs	ext	10hrs	ext	6hrs	ext	4hrs	ext

## APPLICATION AND USE

<b>Preparation</b>	<p><b>NEWBUILDING:</b> Dependant upon yard procedures, consult International Technical Representative.</p> <p><b>MAJOR REFURBISHMENT:</b> The first coat of Superyacht 900 Antifouling should always be applied over a recommended anticorrosive primer system. The primer surface should be dry and free of all contaminants (oil, grease, salt etc) and overcoated with Superyacht 900 Antifouling within the overcoating interval specified for the primer.</p> <p><b>REPAIR and UPGRADING APPROVED SYSTEMS:</b> Degrease the surface. Clean the entire area with controlled high pressure washing (3000 psi./211 bar). Antifouling should only be wet sanded. Never dry sand or burn-off old antifouling. Repair corroded areas with the recommended anticorrosive primer system (Primocon or JVA202).</p>
<b>Method</b>	Ensure the area is clean and dry. Take care to apply all the paint calculated even if it means applying an extra coat (airless spray). It is important for performance to apply the correct thickness. Apply an extra stripe coat in areas of high wear such as chines, rudders, sterngear and any leading edges.
<b>Hints</b>	<p><b>Thinner</b> YTA085 Thinners No.3 or GTA007</p> <p><b>Cleaner</b> YTA085 Thinners No.3</p> <p><b>Airless Spray</b> Pressure: 177-213 bar. Tip Size: 2180-2680.</p>
<b>Some Important Points</b>	Not for use on vessels under 25 m in length. Do not use below 10°C/50°F. Ambient temperature should be minimum 10°C and maximum 35°C. Product temperature should be minimum 10°C and maximum 35°C. Substrate temperature should be minimum 5°C/40°F and maximum 35°C/95°F.

<b>Compatibility/Substrates</b>	Can be applied over Superyacht 800 and 900 Antifoulings worldwide and most tin copolymers. For further details on compatibility consult International Technical Representatives. Prime non-antifoulings with Primocon, Intertuf JVA202 or Interprotect. Not suitable for use over Aluminium/Alloy substrates or zinc sprayed surfaces.
<b>Number of Coats</b>	1-2
<b>Coverage</b>	(Theoretical) - 3.33 (m <sup>2</sup> /lt) (Practical) - 2.50 (m <sup>2</sup> /lt) by spray
<b>Recommended DFT</b>	150 microns dry
<b>Recommended WFT</b>	300 microns wet
<b>Application Methods</b>	Brush, Roller, Airless Spray

## TRANSPORTATION, STORAGE AND SAFETY INFORMATION

<b>Storage</b>	<p><b>GENERAL INFORMATION:</b> Exposure to air and extremes of temperature should be avoided. For the full shelf life of Superyacht 900 Antifouling to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/40°F and 35°C/95°F. Keep out of direct sunlight.</p> <p><b>TRANSPORTATION:</b> Superyacht 900 Antifouling should be kept in securely closed containers during transport and storage.</p>
<b>Safety</b>	<p><b>GENERAL:</b> Contains organotin which may be restricted in use in certain countries or areas. Read the label safety section for Health and Safety Information, also available from our Technical Help Line.</p> <p><b>DISPOSAL:</b> Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.</p> <p>Remainders of Superyacht 900 Antifouling cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.</p>

**IMPORTANT NOTES** *The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal or injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.*

**X** and International are registered trademarks of Akzo Nobel.

## Regional Addresses

<p><b>Head Office</b> International Paint Ltd P O Box 20980 Oriol House 16 Connaught Place London W2 2ZB United Kingdom tel: +44 (0) 171 479 6000 fax: +44 (0) 171 479 6500</p>	<p><b>European Region</b> International Paint Ltd Stoneygate Lane Felling, Gateshead Tyne &amp; Wear NE10 0JY United Kingdom tel: +44 (0) 191 469 6111 fax: +44 (0) 191 438 3977</p>	<p><b>Asia Region</b> International Paint Singapore (Pte) Ltd 449 Tagore Industrial Avenue 01-03 Hong Joo Industrial Building Singapore 787820 tel: +65 6453 1981 fax: +65 6453 1778</p>	<p><b>Australasia Region</b> International Paint 115 Hyde Road Yeronga, Brisbane Queensland 4104 Australia tel: +61 (0) 7 3892 8866 fax: +61 (0) 7 3892 4287</p>	<p><b>North America Region</b> International Paint Inc 2270 Morris Avenue Union New Jersey 07083 USA tel: +1 (0) 908 686 1300 fax: +1 (0) 908 686 8545</p>	<p><b>South America Region</b> International Paint Rod Rap tavares, KM 18.5 Predio Administrativo 11 Butanta CEP 05577-300 Sao Paulo, Brazil tel: +55 (0) 11 3789 2000 fax: +55 (0) 11 3789 2200</p>
---	--	--	--	--	--



Ref: 05000026  
Issue Date: 13-Feb-2003  
Supersedes: 28-Nov-2002