

## PRODUCT DESCRIPTION

Toplac is a premium gloss marine enamel for all substrates above the waterline. It is exceptionally easy to apply by brush or roller and pad and contains UV filter for increased durability.

- \* Excellent flow characteristics
- \* Range of bright colours
- \* Over twice the life of ordinary alkyd enamels

Its unique chemical structure enables Toplac to outperform traditional finishes giving a long lasting high definition gloss.

## PRODUCT INFORMATION

<b>Colour</b>	YKA184-Mediterranean White, YKA187-Ivory, YKA905-White A905, YKB000-Snow White, YKB914-Baltic Blue, YKB993-Oxford Blue, YKE938-Danube Blue, YKF684-Atlantic Grey, YKF991-Mauritius Blue, YKJ292-Bounty, YKS101-Yellow, YKS299-Rochelle Red, YKS936-Lauderdale Blue, YKT541-Donegal Green, YKU898-Bondi Blue, YKY999-Jet Black, YKZ501-Rustic Red . Refer to colour chart for further details.
<b>Finish</b>	High Gloss
<b>Specific Gravity</b>	1.1
<b>Volume Solids</b>	51%
<b>Typical Shelf Life</b>	2 yrs
<b>VOC (As Supplied)</b>	404 g/ltr
<b>Unit Size</b>	750 ml 375 ml (some colours only) 2.5 Lt (some colours only)

## DRYING/OVERCOATING INFORMATION

		Drying			
		5°C	15°C	23°C	35°C
Touch Dry [ISO]		6hrs	3hrs	2hrs	1hrs

		Overcoating							
		Substrate Temperature							
		5°C		15°C		23°C		35°C	
Overcoated By		Min	Max	Min	Max	Min	Max	Min	Max
Toplac		24hrs	4days	16hrs	3days	8hrs	2days	6hrs	1days

## APPLICATION AND USE

### Preparation

#### PREVIOUSLY PAINTED SURFACES:

**In Good Condition:** Wash down with Yacht Line Super Cleaner, rinse with fresh water and allow to dry. Abrade with 280-320 grade (grit) paper.

**In Poor Condition:** Remove all previous coatings and prime the substrate.

**PRIMING:** Substrate preparation is covered separately on the primer datasheet.

**BARE WOOD:** Prime with Yacht Primer or UCP.

**STEEL:** Prime with Yacht Primer or Interprotect.

**ALUMINIUM:** Prime with Etch Primer followed by either Yacht Primer or Interprotect.

**GRP:** Wash down with Yacht Line Super Cleaner, rinse with fresh water and allow to dry. Abrade with 180-220 grade paper.


**AGED/WEATHERED GELCOATS:** Due to the potentially porous nature of aged/weathered gelcoats the risk of solvent/moisture entrapment after painting is much higher than when gelcoat is new. As a result this entrapment could lead to blistering of the paint film. To reduce the risk of paint film blistering it is recommended that 3 coats of Interprotect are applied to seal the gelcoat. Interprotect must be overcoated with Polyurethane Basecoat prior to topcoat application.

**ALL SUBSTRATES:** Use Pre-Kote undercoat. If spray applying Toplac, Pre-Kote must be aged a minimum of 14 days. If this is not possible Polyurethane Basecoat can also be used as an undercoat.

<b>Method</b>	Sand the undercoat smooth with 320-400 grade (grit) wet or dry paper. Remove dust with a dust wipe. Apply 1-2 coats.
<b>Hints</b>	<p><b>Mixing</b> Stir well before use.</p> <p><b>Thinner</b> YTA800,YTA063 Thinner No.1 (Thinner No.10 for spraying)</p> <p><b>Thinning</b> In warm or windy conditions up to 10% of thinners may be added to ease application.</p> <p><b>Cleaner</b> YTA800 Thinners No.1</p> <p><b>Ventilation and Humidity Control</b> Apply in dry, well ventilated conditions. Avoid applying late in the evening as condensation can cause a loss of gloss overnight.</p> <p><b>Conventional Spray</b> Thin 10-25% with Thinners No. 10 to a viscosity of 18-22 secs (BS4) or 16-20 secs (DIN4). Pressure: 3-4 bar. Tip Size: 1.1-1.4 mm. NOTE: Pre-Kote undercoat <b>MUST</b> be aged a minimum of 14 days before application of Toplac.</p> <p><b>Other</b> For lighter colours, mix the first coat of finish 50:50 with the undercoat to improve the depth of colour and opacity. For best results when applying by roller, smooth off with a pad or brush.</p>
<b>Some Important Points</b>	Toplac may discolour if used at temperatures above 80°C. Not suitable for permanently immersed surfaces. Do not use below 5°C. Ambient temperature should be minimum 5°C/40°F and maximum 35°C/95°F. Product temperature should be minimum 15°C and maximum 35°C. Substrate temperature should be minimum 5°C/40°F and maximum 35°C/95°F.
<b>Compatibility/Substrates</b>	Use over suitably prepared and undercoated surfaces or existing paint schemes.
<b>Number of Coats</b>	1-2 by brush
<b>Coverage</b>	<p>(Theoretical) - 13.33 (m²/l)</p> <p>(Practical) - 12.00 (m²/l) by brush, 8 m²/l by spray</p>
<b>Recommended DFT</b>	38 microns dry
<b>Recommended WFT</b>	75 microns wet
<b>Application Methods</b>	Conventional Spray, Brush, Roller

## TRANSPORTATION, STORAGE AND SAFETY INFORMATION

<b>Storage</b>	<p><b>GENERAL INFORMATION:</b></p> <p>Exposure to air and extremes of temperature should be avoided. For the full shelf life of Toplac to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/40°F and 35°C/95°F. Keep out of direct sunlight.</p> <p><b>TRANSPORTATION:</b></p> <p>Toplac should be kept in securely closed containers during transport and storage.</p>
<b>Safety</b>	<p><b>GENERAL:</b> Read the label safety section for Health and Safety Information, also available from our Technical Help Line.</p> <p><b>DISPOSAL:</b> Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.</p> <p>Remainders of Toplac cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.</p>

<b>IMPORTANT NOTES</b>	<p><i>The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal or injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.</i></p> <p> and International are registered trademarks of Akzo Nobel.</p>
------------------------	---

## Regional Addresses

<p><b>Head Office</b>  International Paint Ltd  P O Box 20980  Oriol House  16 Connaught Place  London W2 2ZB  United Kingdom  tel: +44 (0) 171 479 6000  fax: +44 (0) 171 479 6500</p>	<p><b>European Region</b>  International Paint Ltd  Stoneygate Lane  Felling, Gateshead  Tyne &amp; Wear NE10 0JY  United Kingdom  tel: +44 (0) 191 469 6111  fax: +44 (0) 191 438 3977</p>	<p><b>Asia Region</b>  International Paint Singapore  (Pte) Ltd  449 Tagore Industrial Avenue  01-03 Hong Joo Industrial  Building  Singapore 787820  tel: +65 6453 1981  fax: +65 6453 1778</p>	<p><b>Australasia Region</b>  International Paint  115 Hyde Road  Yeronga, Brisbane  Queensland 4104  Australia  tel: +61 (0) 7 3892 8866  fax: +61 (0) 7 3892 4287</p>	<p><b>North America Region</b>  International Paint Inc  2270 Morris Avenue  Union  New Jersey 07083  USA  tel: +1 (0) 908 686 1300  fax: +1 (0) 908 686 8545</p>	<p><b>South America Region</b>  International Paint  Rod Rap tavares, KM 18.5  Predio Administrativo 11  Butanta CEP 05577-300  Sao Paulo, Brazil  tel: +55 (0) 11 3789 2000  fax: +55 (0) 11 3789 2200</p>
---	---	--	---	---	---