

## **Epifanes Woodfinish Matte**

## Matte finish with breathing properties

**Type** Airdrying

Base Alkyd / urethane resin / tung oil

Properties A clear, satin finish providing a beautiful, rich, matte finish for all fine

woodworks, like teak and iroco, giving years of protection against alcohol

and other aggresive household chemicals.

Field of application Apply as a finish coat over several build-up coats of Epifanes Woodfinish

gloss or Epifanes Clear Gloss Varnish.

**Colour** Amber clear

**Gloss** Rich satin sheen

**Density** 0,95kg/dm³

Viscosity 100 seconds DIN-cup 4 mm.

Solids contents 52 +/- 2 %

 VOC-level
 474 gram / liter

 Packing
 500ml. - 1000ml.

Shelf life In closed container stored in a dark location between 5-25°C.,

approx. 3 years

Conditions duringTemperatureminimal 8°C. - maximum 28°C.application and dryingRelative air humidityminimal 50% - maximum 75%

BrushthinnerEpifanes Brushthinner for Paint & VarnishSpraythinnerEpifanes Spraythinner for Paint & Varnish

Application tools Soft, longhaired brush (oval or full style) and conventional air spray

Recommended filmthickness

per coat

60-70 μm wetfilmthickness = 30-35 μm dryfilmthickness

Application recommendations Do not overbrush. Do not apply wet-in-wet. Apply along the wood grain

and do not apply excessive wet films to avoid the formation of curtains and drying problems. Avoid varnishing in direct sunlight or too much wind. A rapid loss of solvents will occur under these conditions and decrease the flowing ability. Use only soft, long bristled, clean and dry brushes of

good quality.

Theoretical coverage 13 m<sup>2</sup> per litre @ 30 µm dry filmthickness

Practicle coverage Dependent on condition of substrate, loss of material due to factors such

as application technique, shape of object, circumstances during

application.

Substrate conditions Bare wood, dry, well degreased and sanded, percentage of humidity

inside the wood < 15%. Well cleaned, degreased, sanded, intact well

adhering one- and two-component varnish systems.



## **Epifanes Woodfinish Matte**

## Matte finish with breathing properties

Application details

	Air spra□	Br⊡sh
Thinning volume	15-15 %	0-5%
ole	1. mm - 1.5 mm	
Pressure	2 - 3 ar	
Viscosity DI -cup mm	20-4 sec.	

Application remarks

Airless spray not advised

Drying times @ 20°C. / 65% RAH and 30 µm dry filmthickness

D⊡stdr□	Sandab@	Re <b>⊡oatab</b> e
1 hour	1 hours	1 hours

Recoatability with

Epifanes Rubbed Effect Varnish Epifanes Clear Gloss Varnish

Epifanes Rapidclear Epifanes Rapidcoat

System build up interior

Prod□□t	Nbr. of ⊡oats	Epifanes Thinner per <b>□oa</b> t		Dr⊡ing ti⊡ es per ⊡oat at □□C.□□F	Abrasi⊡e paper	Re□ ar <b></b> s
EPIAES Woodfinish Gloss	1	EPIAES Brushthinner for Paint & Varnish	25	4 hours	0 dr	Alternative build up with Epifanes Clear Gloss Varnish
EPIAES Woodfinish Gloss	3	EPIAES Brushthinner for Paint & Varnish	5-10	4 hours	0 dr	Grain filling and sealing coats. n open- poric wood types more grain filling coats may be needed. Sand by hand along the wood grain.
EPIAES Woodfinish Matte	1	EPIAES Brushthinner for Paint & Varnish	0-5	2 hours	280 dry	Sand by hand along the wood grain.
Total number of coats	5					

Svstem	build up	exterior

Lind India Contains tresons are antiched by analysin this finish and a containing the sentence of the containing and the conta

Safety

The user of this product should obey all all national laws and legislation concerning health, safety and environmental haard. or more information on health and safeTy, refer to the Material Safety Data Sheet of this product.

Allthough the facts and suggestions in this product information sheet are based on our own research and field experiences and are believed reliable, we cannot simply be held responsible for performance or results obtained through the use of this product. Ineffectiveness or other unintended consequences may result, because of such factors as weather, conditions, presence or other materials or the manner of preparation, use or application all of which are beyond W. eeren & oo n's control. All such risks are assumed by user.

DISC\_AIMER OF WARRANTIES. Seller maes no epress arranties. TE IMPIED WARRATIES MERCATABIIT AD ITESS R A PARTICAR PRPSE ARE ECDED. In the event a warranty is crea ECSIVE REMED shall be the replacement of any defective product. o other remedy (including, but not limited to, incident sales, injury to person or property, or any other incidental or consequential loss) shall be available to buyer.

ted la uers al or consequential damages for lost profits, lost

Septe ber