

Intertuf 16

Primers

Narrowboat Blacking



PRODUCT DESCRIPTION

Intertuf 16 is specifically developed for the economical protection of steel. This tough, non-cracking coating offers protection against rust and is ideal for Narrowboat Blacking.

- * Economical protection for steel
- * Tough, non-cracking formulation
- * Chemically resistant to mild acids and alkalis

PRODUCT INFORMATION

Colour	JBA016-Black
Finish	Not Applicable
Specific Gravity	1.0
Volume Solids	53%
Typical Shelf Life	2 yrs
Unit Size	2.5 Lt

DRYING/OVERCOATING INFORMATION

	Drying					
	5°C (41°F)		23°C (73°F)		35°C (95°F)	
Touch Dry	24 hrs		8 hrs		8 hrs	
Hard Dry	3 days		2 days		2 days	

	Overcoating					
	Substrate Temperature					
	5°C (41°F)		23°C (73°F)		35°C (95°F)	
Overcoated By	Min	Max	Min	Max	Min	Max
Intertuf 16	24 hrs	ext	8 hrs	ext	8 hrs	ext

APPLICATION AND USE

Preparation	EXTERIOR HULL COATING: STEEL: Remove any rust with 60-80 grade abrasive paper and remove all dust. PREVIOUSLY PAINTED SURFACES: Sand surface with 120-150 grade (grit) paper and remove all dust.
Method	Apply 2-3 coats (spray) or 4-5 coats (brush).
Hints	Mixing Stir well before use. Thinner YTA800 Thinners No.1. Thinning is not required and should only be used in exceptional circumstances. Cleaner YTA800 Thinners No.1 Ventilation and Humidity Control Apply in a well ventilated area. Airless Spray Pressure: 176-210 bar. Tip Size: 1880-2680. Other Leave until completely dry (min. 3 days @ 15°C).
Some Important Points	Product temperature should be minimum 5°C/41°F and maximum 35°C/95°F. Ambient temperature should be minimum 5°C/41°F and maximum 35°C/95°F. Substrate temperature should be minimum 5°C/41°F and maximum 35°C/95°F.
Compatibility/Substrates	Suitable for steel or previously painted surfaces. Not suitable for GRP or alloy.
Number of Coats	Apply 2-3 coats (spray) or 4-5 coats (brush).
Coverage	(Theoretical) - 10.0 m ² /lt by brush, 5.3 m ² /lt by spray (Practical) - 9.0 m ² /lt by brush, 3.2 m ² /lt by spray
Recommended DFT per coat	53 microns dry by brush / roller, 100 microns dry by spray
Recommended WFT per coat	110 microns wet by brush / roller, 215 microns wet by spray
Application Methods	Airless Spray, Brush, Roller Application by brush is recommended for stripe coats and small areas only. Multiple coats may be required to achieve specified film thickness.

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage	GENERAL INFORMATION: Exposure to air and extremes of temperature should be avoided. For the full shelf life of Intertuf 16 to be realised ensure
----------------	--

Please refer to your local representative or visit <http://www.yachtpaint.com> for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2014.

Intertuf 16
Primers
Narrowboat Blacking



that between use the container is firmly closed and the temperature is between 5°C/41°F and 35°C/95°F. Keep out of direct sunlight.

TRANSPORTATION:

Intertuf 16 should be kept in securely closed containers during transport and storage.

Safety

GENERAL:

Read the label safety section for Health and Safety Information, also available from our Technical Help Line.

DISPOSAL:

Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.

Remainders of Intertuf 16 cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.

IMPORTANT NOTES

The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

Please refer to your local representative or visit <http://www.yachtpaint.com> for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2014.