



## Technical Data Sheet

<b>PRODUCT NAME:</b>	<b>KARMA VT</b>																								
<b>DESCRIPTION:</b>	Karma VT Vinyl Tar a single pack structured coating based on a highly acid and alkali resisting medium which in combination with special coal tar pitch gives a high build moisture repellent anti corrosive coating. Karma VT dries to a pleasant slight sheen.																								
<b>KEY FEATURES:</b>	Long term protection for steel and concrete. Suitable for immersion conditions (Not Potable Water) Abrasion Resistant Flexible. Has excellent oil and diesel resistance. Single pack, no pot life problems. Ease of application.																								
<b>USE:</b>	Having excellent weather and abrasion resistance, allied to excellent oil & diesel resistance Karma VT will provide long term protection to steel and concrete. Easy to apply, Karma VT is suitable for use in both fresh and saline conditions. .																								
<b>SURFACE PREPARATION:</b>	<b>New Work:</b> Clean/de-rust to bright metal. Abrade with coarse wet & dry. Degrease. <b>Refurbishment:</b> Pressure clean; de-rust as required and patch treat before full application.																								
<b>APPLICATION:</b>	Apply by brush; roller or airless spray. Use as supplied; if required thin with Xylene. Apply 3 coats on new work; 1-2 coats on refurbishment Minimum application temperature: 10°C <b>Karma VT is for Professional Use Only</b>																								
<b>DRYING/OVERCOATING:</b>	<table><tr><td>Touch Dry (15°C)</td><td>1 hour</td></tr><tr><td>Hard Dry (15°C)</td><td>4 hours</td></tr><tr><td>Overcoating time(15°C)</td><td>24 hours</td></tr><tr><td>Launch time</td><td>48 hours</td></tr></table>	Touch Dry (15°C)	1 hour	Hard Dry (15°C)	4 hours	Overcoating time(15°C)	24 hours	Launch time	48 hours																
Touch Dry (15°C)	1 hour																								
Hard Dry (15°C)	4 hours																								
Overcoating time(15°C)	24 hours																								
Launch time	48 hours																								
<b>PHYSICAL PROPERTIES:</b>	<table><tr><td>Mixing Ratio</td><td>Single pack product</td></tr><tr><td>Thinner/Cleaner</td><td>Xylene</td></tr><tr><td>Supply SG</td><td>1.15 typical</td></tr><tr><td>Colour</td><td>Black, Brown</td></tr><tr><td>Gloss Level</td><td>Slight Gloss</td></tr><tr><td>Theoretical Coverage:</td><td>3.5 – 4.5 square metres per litre per coat</td></tr><tr><td>Dry Film Thickness:</td><td>For 100 microns D.F.T apply Wet Film Thickness of 200 microns. For 125 microns D.F.T apply Wet Film Thickness of 280 microns.</td></tr><tr><td>VOC Content:</td><td>481 grammes per litre</td></tr><tr><td>Flash Point / Class / UN No</td><td>≥21°C / III / UN 1263</td></tr><tr><td>Pack Size</td><td>5 litre containers</td></tr><tr><td>Shelf Life</td><td>12 months unopened, stored at UK ambient temperatures.</td></tr><tr><td>Health &amp; safety:</td><td>Refer to Product Safety Data Sheet before use.</td></tr></table>	Mixing Ratio	Single pack product	Thinner/Cleaner	Xylene	Supply SG	1.15 typical	Colour	Black, Brown	Gloss Level	Slight Gloss	Theoretical Coverage:	3.5 – 4.5 square metres per litre per coat	Dry Film Thickness:	For 100 microns D.F.T apply Wet Film Thickness of 200 microns. For 125 microns D.F.T apply Wet Film Thickness of 280 microns.	VOC Content:	481 grammes per litre	Flash Point / Class / UN No	≥21°C / III / UN 1263	Pack Size	5 litre containers	Shelf Life	12 months unopened, stored at UK ambient temperatures.	Health & safety:	Refer to Product Safety Data Sheet before use.
Mixing Ratio	Single pack product																								
Thinner/Cleaner	Xylene																								
Supply SG	1.15 typical																								
Colour	Black, Brown																								
Gloss Level	Slight Gloss																								
Theoretical Coverage:	3.5 – 4.5 square metres per litre per coat																								
Dry Film Thickness:	For 100 microns D.F.T apply Wet Film Thickness of 200 microns. For 125 microns D.F.T apply Wet Film Thickness of 280 microns.																								
VOC Content:	481 grammes per litre																								
Flash Point / Class / UN No	≥21°C / III / UN 1263																								
Pack Size	5 litre containers																								
Shelf Life	12 months unopened, stored at UK ambient temperatures.																								
Health & safety:	Refer to Product Safety Data Sheet before use.																								

**CLEANUP:**

All equipment should be cleaned immediately after use with Xylene.

Waste materials, including packaging, must be disposed of in accordance with local regulations.

**HEALTH AND SAFETY:**

Care must be taken to avoid inhaling the concentrated solvent vapours. Refer to Product Safety Data Sheet before use. Gloves and if possible, eye shields should be worn for mixing and any splashes on the skin should be washed off immediately with soap and water. If spraying is carried out masks should be worn and good ventilation provided.

The solvent vapour forms an explosive mixture with air and no naked light of any kind should be allowed in the vicinity. **Smoking Must Be Prohibited.**

*This information is given in good faith for the guidance of users, but is without warranty or liability. Any queries should be referred to our technical department,*

**Karma Coatings Limited**

2 Sefton Road, Litherland, Liverpool, L21 7PG

Tel: 0151 284 9091 Fax: 0151 284 3305 Email: [sales@karmacoatings.co.uk](mailto:sales@karmacoatings.co.uk)