

Codice: ZQT &amp; ZRT

# Topkapi

## POLYURETHANE ONE-COMPONENT GLOSS TOPCOAT



One-component, polyurethane gloss non-yellowing topcoat of superior quality for a long lasting brilliant finish of boats. High coverage, weather resistance in marine environment, and pure colours make of this product the best choice for a high quality one-component finish. Available in a wide range of special marine colours for an excellent spray or brush finish application (see colour card).

### Technical Characteristics

<b>Paint Type</b>	One component
<b>Binder type A</b>	Alkyd-urethane
<b>Specific gravity kg/lit (±0,05)</b>	1,000-1,215 secondo il colore
<b>Solids content (volume) ±2</b>	53%
<b>Viscosity Ford ø 8 at 20°C ±2</b>	14-16
<b>Shelf life (+10+30°C)</b>	18 months in airtight cans

### Application Data

<b>Application</b>	Brush-Roller-Spray
<b>Brush-Roller</b>	10-20% Diluent 107 or 109
<b>Spray</b>	10-25% Diluent 900
<b>Touch dry</b>	2-3 h (20°C)
<b>Recoat time</b>	18-24 h (20°C)
<b>Application temperature</b>	Between +10 C et +40 C
<b>Relevant humidity</b>	Less than 80%
<b>Dry film thickness advised</b>	40-50 microns by hand
<b>Theoret. coverage m2/Lt</b>	11-13

## SURFACE PREPARATION AND APPLICATION

### Bare Steel.

The substrate should be clean, dry and well degreased. Remove traces of corrosion and apply 1 coat of suitable primer (e.g. SOTTOFONDO NAUTICA or CROMOMINIO-AT) and let dry. Overcoat with 2 coats of TOPKAPI ENAMEL allowing 18-24 hours between coats.

### Bare Wood.

The surface should be clean, dry and well seasoned. If necessary apply one coat of POLIGLASS VARNISH diluted 50-70% or more, or LIGNUM IMPREGNANTE as alternative, without build up a film on the surface. After 24 hours apply 1 coat of SOTTOFONDO NAUTICA and let dry for 24 hours. Overcoat with 2 coats of TOPKAPI ENAMEL allowing 24 hours between coats.

### Previously Painted Surfaces.


Loose or powdery old paints should be mechanically removed. Clean the surface well and follow application directions as per bare substrat. If the old paint is in good condition and it only needs a topcoat because it is dull or dirty but with the underneath coatings still well fixed to the substrate (with no cracks or bubbles), degrease and sandpaper with fine abrasive paper the surface; remove dust, clean well and apply 2 coats of TOPKAPI ENAMEL allowing 24 hours between coats.

Codice: 2QT & 2RT

# Topkapi

Note: In the summer season or when temperatures are higher than 20°C, it is recommended for brush application the use of FLOWING THINNER 109.

## Colors




Colore: BIANCO  
Cod. Colore: 2QT080




Colore: NERO GONDOLA  
Cod. Colore: 2QT070




Colore: GHIACCIO  
Cod. Colore: 2QT020



Colore: AVORIO  
Cod. Colore: 2QT050



Colore: MARRONE  
Cod. Colore: 2QT108



Colore: GRIGIO CHIARO  
Cod. Colore: 2QT116



Colore: GRIGIO MEDIO  
Cod. Colore: 2QT119



Colore: AZZURRO CIELO  
Cod. Colore: 2QT121




Colore: AZZURRO LUMINOSO  
Cod. Colore: 2QT124



Colore: BLU OCEANO  
Cod. Colore: 2QT122



Colore: VERDE SMERALDO  
Cod. Colore: 2QT126



Colore: GIALLO CROMO  
Cod. Colore: 2QT110



Colore: ROSSO VIVO  
Cod. Colore: 2RT113



Colore: BLU MARINO  
Cod. Colore: 2QT142

## Listino

### Formati Disponibili

2.5L

0.75L

### Codice

### Descrizione

### Confezione

2QT02000750	Topkapi ghiaccio 020	0.75 lt
2QT05000750	Topkapi avorio 050	0.75 lt
2QT07000750	Topkapi nero gondola 070	0.75 lt
2QT08000750	Topkapi bianco 080	0.75 lt
2QT08002500	Topkapi bianco 080	2.50 lt
2QT10800750	Topkapi marrone 108	0.75 lt
2QT11600750	Topkapi grigio chiaro 116	0.75 lt
2QT11900750	Topkapi grigio medio 119	0.75 lt
2QT12100750	Topkapi azzurro cielo 121	0.75 lt

Codice	Descrizione	Confezione
2QT12200750	Topkapi blue oceano 122	0.75 lt
2QT12400750	Topkapi azzurro luminoso 124	0.75 lt
2QT12600750	Topkapi verde smeraldo 126	0.75 lt
2QT14200750	Topkapi blue marino 142	0.75 lt
2QT14202500	Topkapi blue marino 142	2.50 lt
2RT11000750	Topkapi giallo cromo 110	0.75 lt
2RT11300750	Topkapi rosso vivo 113	0.75 lt
2RT11302500	Topkapi rosso vivo 113	2.50 lt

**SAFETY PRECAUTIONS**

Before starting paint application attention should be paid to the symbols of risk specified on the label of each can. Please carefully read all the safety precautions advised on the label, or in the safety data sheet available on request at [laboratorio@aemmecolori.it](mailto:laboratorio@aemmecolori.it)

**NOTES**

This information is provided to the best of our current knowledge, however, because the conditions of use of our products are beyond our control, this information does not constitute any kind of implied warranties; in that sense the supplying company accepts from now responsibility that can be connected to an abnormal use of the products. The Engineering Department at your location is available for any questions related to the use of our products. The percentages of dilution and the drying time are to be considered only indicative, in relation to a temperature of 20 ° C and are therefore subject to change with the change of temperature, in the presence of particular weather conditions or application determining factors at the time of application.