

PRODUCT DESCRIPTION

A matting additive specially formulated for mixing with International one pack finishes (Interlux Super and Toplac) and varnishes (Original, Goldspar and Schooner) to produce a variety of gloss, satin or matt effect finishes. For interior and exterior use.

PRODUCT INFORMATION

Colour	YMA715-Translucent
Specific Gravity	1.0
Volume Solids	48%
Typical Shelf Life	2 yrs
Unit Size	750 ml

DRYING/OVERCOATING INFORMATION

Drying

Overcoating Substrate Temperature

Overcoated By	Min	Max	Min	Max	Min	Max	Min	Max
---------------	-----	-----	-----	-----	-----	-----	-----	-----

APPLICATION AND USE

Preparation	Follow the surface preparation instructions shown on the label of the finish or varnish to which the Matting Additive is being added.
Method	Stir individual products prior to mixing. The level of gloss will decrease where the amount of Matting Additive is increased. The opacity of the chosen finish will be affected once the clear Matting Additive is added. Apply the standard finish first and finish off with the mixed (matted) material as a last coat, or apply multiple coats until full opacity is achieved. Stir well before use.
Hints	<p>Mixing GUIDELINES ARE AS FOLLOWS: Toplac: 25% addition of the Matting Additive by volume = 79% gloss . 50% addition of the Matting Additive by volume = 26% gloss . 75% addition of the Matting Additive by volume = 8% gloss . Interlux Super: 25% addition of the Matting Additive by volume = 66% gloss . 50% addition of the Matting Additive by volume = 49% gloss . 75% addition of the Matting Additive by volume = 37% gloss. All gloss levels refer to measurements using a 60° head.</p> <p>Thinner YTA800 Thinners No.1</p> <p>Thinning Thin 5% with Thinners No. 1 if required.</p> <p>Conventional Spray Pressure: 3-4 bar. Tip Size: 1.1-1.4 mm. For spray application of matted 1-pack varnishes or finishes, follow instructions on the datasheet for the product in question.</p> <p>Other The addition of Matting Additive to a finish or varnish will not affect the drying or overcoating characteristics of the product. It will not affect the durability of the finished surface. As with all the types of reduced-gloss coatings, the resulting finish will not have the same stay-clean properties as a full-gloss coating. If all the mixed (matted) material is not used it may be used at a later date. Simply stir well before use.</p>
Some Important Points	Product temperature should be minimum 15°C/60°F and maximum 30°C/86°F. Ambient temperature should be minimum 5°C/40°F and maximum 35°C/95°F. Substrate temperature should be minimum 5°C/40°F and maximum 35°C/95°F.
Compatibility/Substrates	Only suitable for use with 1-pack varnishes or finishes.

Number of Coats Variable

Recommended DFT

Application Methods Brush, Roller, Conventional Spray

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage

GENERAL INFORMATION:

Exposure to air and extremes of temperature should be avoided. For the full shelf life of Matting Additive to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/40°F and 35°C/95°F. Keep out of direct sunlight.

TRANSPORTATION:

Matting Additive should be kept in securely closed containers during transport and storage.

Safety

GENERAL: Read the label safety section for Health and Safety Information, also available from our Technical Help Line.

DISPOSAL: Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.

Remainders of Matting Additive cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.

IMPORTANT NOTES

The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal or injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

X and International are registered trademarks of Akzo Nobel.

Regional Addresses

Head Office

International Paint Ltd
P O Box 20980
Oriol House
16 Connaught Place
London W2 2ZB
United Kingdom
tel: +44 (0) 171 479 6000
fax: +44 (0) 171 479 6500

European Region

International Paint Ltd
Stoneygate Lane
Felling, Gateshead
Tyne & Wear NE10 0JY
United Kingdom
tel: +44 (0) 191 469 6111
fax: +44 (0) 191 438 3977

Asia Region

International Paint Singapore
(Pte) Ltd
449 Tagore Industrial Avenue
01-03 Hong Joo Industrial
Building
Singapore 787820
tel: +65 6453 1981
fax: +65 6453 1778

Australasia Region

International Paint
115 Hyde Road
Yeronga, Brisbane
Queensland 4104
Australia
tel: +61 (0) 7 3892 8866
fax: +61 (0) 7 3892 4287

North America Region

International Paint Inc
2270 Morris Avenue
Union
New Jersey 07083
USA
tel: +1 (0) 908 686 1300
fax: +1 (0) 908 686 8545

South America Region

International Paint
Rod Rap tavares, KM 18.5
Predio Administrativo 11
Butanta CEP 05577-300
Sao Paulo, Brazil
tel: +55 (0) 11 3789 2000
fax: +55 (0) 11 3789 2200



Ref: 05000134
Issue Date: 4-Sep-2004
Supersedes: 14-Feb-2003