

PRODUCT DESCRIPTION

Wood primer for use above and below the waterline. Also suitable as an antifouling sealer for incompatible antifoulings.

PRODUCT INFORMATION

Colour	YPA701-Pink Metallic
Finish	Matt
Specific Gravity	1.5
Volume Solids	53%
Typical Shelf Life	2 yrs
Unit Size	750 ml 2.5 Lt

DRYING/OVERCOATING INFORMATION

	Drying							
	5°C		15°C		23°C		35°C	
Touch Dry [ISO]	24hrs		10hrs		6hrs		3hrs	

Overcoated By	Overcoating							
	Substrate Temperature							
	5°C		15°C		23°C		35°C	
	Min	Max	Min	Max	Min	Max	Min	Max
Boatgard	36hrs	1mths	24hrs	1mths	16hrs	1mths	12hrs	1mths
Cruiser Premium	36hrs	1mths	24hrs	1mths	16hrs	1mths	12hrs	1mths
Interdeck	36hrs	1mths	24hrs	1mths	16hrs	1mths	12hrs	1mths
Interlux Super	36hrs	1mths	24hrs	1mths	16hrs	1mths	12hrs	1mths
Interspeed Ultra	36hrs	1mths	24hrs	1mths	16hrs	1mths	12hrs	1mths
Metallic Pink Primer	36hrs	1mths	24hrs	1mths	16hrs	1mths	12hrs	1mths
Micron Extra	36hrs	1mths	24hrs	1mths	16hrs	1mths	12hrs	1mths
Micron Optima	36hrs	1mths	24hrs	1mths	16hrs	1mths	12hrs	1mths
Pre-Kote	36hrs	1mths	24hrs	1mths	16hrs	1mths	12hrs	1mths
Toplac	36hrs	1mths	24hrs	1mths	16hrs	1mths	12hrs	1mths
Trilux	36hrs	1mths	24hrs	1mths	16hrs	1mths	12hrs	1mths
Waterways	36hrs	1mths	24hrs	1mths	16hrs	1mths	12hrs	1mths

Note: If used as a barrier coat leave for 7 days before overcoating. If maximum overcoating times are exceeded, sand using 180 grade paper.

APPLICATION AND USE

Preparation	BARE WOOD: Ensure bare wood is clean and dry. Apply UCP or alternatively 1 coat of Metallic Pink Primer thinned 10-15% with Thinners No.1 to ensure penetration and adhesion. OILY WOODS e.g. Teak: Wash surface with Thinners No 1, allow to dry. Thin first coat of Metallic Pink Primer 10 - 15% prior to application.
Method	Apply 4 full coats to provide a sound protective base for any conventional (one-pack) finish. Fill after first coat if necessary. If used as a barrier coat leave for 7 days before overcoating.
Hints	Thinner YTA800 Thinners No.1 Airless Spray Pressure: 211 bar. Tip Size: 2180-2680.
Some Important Points	Do not overcoat with 2-component solvent-based products. Do not use below 5°C. Product temperature should be minimum 5°C/40°F and maximum 35°C/95°F. Ambient temperature should be minimum 5°C/40°F and maximum 35°C/95°F. Substrate temperature should be minimum 5°C/40°F and maximum 35°C/95°F.
Compatibility/Substrates	Suitable for all types of wood.

Number of Coats	4
Coverage	(Theoretical) - 10.60 (m ² /lt)
Recommended DFT	45 microns dry
Recommended WFT	85 microns wet
Application Methods	Brush, Roller, Airless Spray

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage	<p>GENERAL INFORMATION: Exposure to air and extremes of temperature should be avoided. For the full shelf life of Metallic Pink Primer to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/40°F and 35°C/95°F. Keep out of direct sunlight.</p> <p>TRANSPORTATION: Metallic Pink Primer should be kept in securely closed containers during transport and storage.</p>
Safety	<p>GENERAL: Read the label safety section for Health and Safety Information, also available from our Technical Help Line.</p> <p>DISPOSAL: Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.</p> <p>Remainders of Metallic Pink Primer cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.</p>

IMPORTANT NOTES *The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal or injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.*

X and International are registered trademarks of Akzo Nobel.

Regional Addresses

<p>Head Office International Paint Ltd P O Box 20980 Oriol House 16 Connaught Place London W2 2ZB United Kingdom tel: +44 (0) 171 479 6000 fax: +44 (0) 171 479 6500</p>	<p>European Region International Paint Ltd Stoneygate Lane Felling, Gateshead Tyne & Wear NE10 0JY United Kingdom tel: +44 (0) 191 469 6111 fax: +44 (0) 191 438 3977</p>	<p>Asia Region International Paint Singapore (Pte) Ltd 449 Tagore Industrial Avenue 01-03 Hong Joo Industrial Building Singapore 787820 tel: +65 6453 1981 fax: +65 6453 1778</p>	<p>Australasia Region International Paint 115 Hyde Road Yeronga, Brisbane Queensland 4104 Australia tel: +61 (0) 7 3892 8866 fax: +61 (0) 7 3892 4287</p>	<p>North America Region International Paint Inc 2270 Morris Avenue Union New Jersey 07083 USA tel: +1 (0) 908 686 1300 fax: +1 (0) 908 686 8545</p>	<p>South America Region International Paint Rod Rap tavares, KM 18.5 Predio Administrativo 11 Butanta CEP 05577-300 Sao Paulo, Brazil tel: +55 (0) 11 3789 2000 fax: +55 (0) 11 3789 2200</p>
---	--	--	--	--	--



Ref: 05000133
Issue Date: 13-Nov-2002
Supersedes: 11-Oct-2001