

## PRODUCT DESCRIPTION

Offers protection against fouling in fresh water areas where a hard, scrubbable finish is required.

- \* Suitable for fresh water and other areas of light fouling
- \* Hard, scrubbable surface
- \* Can be applied over most antifoulings provided they are in sound condition

## PRODUCT INFORMATION

<b>Colour</b>	YBA328-Mid Blue, YBA346-Bright Red
<b>Finish</b>	Matt
<b>Specific Gravity</b>	1.5
<b>Volume Solids</b>	47% average
<b>Typical Shelf Life</b>	2 yrs
<b>Unit Size</b>	2.5 Lt

## DRYING/OVERCOATING INFORMATION

	Drying			
	5°C	15°C	23°C	35°C
Touch Dry [ISO]	1hrs	45mins	30mins	20mins
Immersion	24hrs	12hrs	8hrs	6hrs

**Note:**Max. Immersion Times are as follows: 5°C - 6 wks; 15°C - 3 wks; 23-35°C - 1 wk

	Overcoating							
	Substrate Temperature							
	5°C		15°C		23°C		35°C	
Overcoated By	Min	Max	Min	Max	Min	Max	Min	Max
Waterways	16hrs	ext	10hrs	ext	6hrs	ext	4hrs	ext

## APPLICATION AND USE

<b>Preparation</b>	<p><b>PREVIOUSLY ANTIFOULING SURFACE:</b></p> <p><b>In Good Condition:</b> Rinse with fresh water and allow to dry. If old antifouling is incompatible or unknown, seal with Primocon.</p> <p><b>In Poor Condition:</b> Use Interstrip to remove all traces of antifouling.</p> <p><b>PRIMING:</b> All preparation for bare substrates is covered on the appropriate primer datasheet.</p> <p><b>BARE GRP:</b> Gelshield 200 for osmosis protection, or Primocon.</p> <p><b>STEEL/IRON:</b> Prime with Interprotect or Primocon.</p> <p><b>LEAD:</b> Etch Primer followed by Interprotect or Primocon.</p> <p><b>WOOD:</b> Preserve, if required, with Intertox. Prime with Interprotect or Primocon.</p>
<b>Method</b>	Apply two coats per season.
<b>Hints</b>	<p><b>Mixing</b> Stir well before use.</p> <p><b>Thinner</b> YTA085 Thinners No.3</p> <p><b>Thinning</b> Thinning is not recommended.</p> <p><b>Cleaner</b> YTA085 Thinners No.3</p> <p><b>Airless Spray</b> Pressure: 176-210 bar. Tip Size: 2180.</p> <p><b>Other</b> For Airmix spray application: Pressure: 2.5 bar. Tip Size: 20-113. True colour will develop after immersion. Take care to apply all the paint calculated even if it means applying an extra coat. It is important for performance to apply the correct thickness.</p>
<b>Some Important Points</b>	To prevent premature failure, ensure the correct amount of paint is applied using the coverage as a guide. Product temperature should be minimum -5°C and maximum 35°C. Ambient temperature should be minimum -5°C and maximum 35°C. Substrate temperature should be minimum 1°C above dew point and maximum 35°C.

<b>Compatibility/Substrates</b>	GRP, Wood, Steel/Iron, Lead. Not suitable for use over Aluminium/Alloy substrates or zinc sprayed surfaces. Can be applied direct over most types of antifoulings, provided they are in sound condition.
<b>Number of Coats</b>	2-3 by brush/roller
<b>Coverage</b>	(Theoretical) - 8.50 (m <sup>2</sup> /lt) by brush; 3.0 m <sup>2</sup> /lt spray.
<b>Recommended DFT</b>	50 microns dry
<b>Recommended WFT</b>	106 microns wet
<b>Application Methods</b>	Airless Spray, Airmix, Brush, Roller

## TRANSPORTATION, STORAGE AND SAFETY INFORMATION

<b>Storage</b>	<p><b>GENERAL INFORMATION:</b> Exposure to air and extremes of temperature should be avoided. For the full shelf life of Waterways to be realised ensure that between use the container is firmly closed and the temperature is between 5° C/40°F and 35°C/95°F. Keep out of direct sunlight.</p> <p><b>TRANSPORTATION:</b> Waterways should be kept in securely closed containers during transport and storage.</p>
<b>Safety</b>	<p><b>GENERAL:</b> Contains biocides. Antifoulings should only be wet sanded. Never dry sand or burn-off old antifoulings. Read the label safety section for Health and Safety Information, also available from our Technical Help Line.</p> <p><b>DISPOSAL:</b> Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.</p> <p>Remainders of Waterways cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.</p>

**IMPORTANT NOTES** *The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal or injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.*

**X** and International are registered trademarks of Akzo Nobel.

## Regional Addresses

<p><b>Head Office</b> International Paint Ltd P O Box 20980 Oriol House 16 Connaught Place London W2 2ZB United Kingdom tel: +44 (0) 171 479 6000 fax: +44 (0) 171 479 6500</p>	<p><b>European Region</b> International Paint Ltd Stoneygate Lane Felling, Gateshead Tyne &amp; Wear NE10 0JY United Kingdom tel: +44 (0) 191 469 6111 fax: +44 (0) 191 438 3977</p>	<p><b>Asia Region</b> International Paint Singapore (Pte) Ltd 449 Tagore Industrial Avenue 01-03 Hong Joo Industrial Building Singapore 787820 tel: +65 6453 1981 fax: +65 6453 1778</p>	<p><b>Australasia Region</b> International Paint 115 Hyde Road Yeronga, Brisbane Queensland 4104 Australia tel: +61 (0) 7 3892 8866 fax: +61 (0) 7 3892 4287</p>	<p><b>North America Region</b> International Paint Inc 2270 Morris Avenue Union New Jersey 07083 USA tel: +1 (0) 908 686 1300 fax: +1 (0) 908 686 8545</p>	<p><b>South America Region</b> International Paint Rod Rap tavares, KM 18.5 Predio Administrativo 11 Butanta CEP 05577-300 Sao Paulo, Brazil tel: +55 (0) 11 3789 2000 fax: +55 (0) 11 3789 2200</p>
---	--	--	--	--	--



Ref: 0500067  
Issue Date: 13-Nov-2002  
Supersedes: 11-Oct-2001