

## PRODUCT DESCRIPTION

Interdeck provides an excellent slip resistant finish. It contains a fine aggregate and will apply easily on all substrates.

\* Low sheen finish prevents dazzling reflected sunlight off decks

\* Easy application

\* Available in a range of colours

The tough polyurethane resin protects decks against everyday wear and tear.

## PRODUCT INFORMATION

<b>Colour</b>	YJB000-White, YJB339-Light Blue, YJB923-Squall Blue, YJC089-Cream
<b>Finish</b>	Low sheen
<b>Specific Gravity</b>	1.4
<b>Volume Solids</b>	54%
<b>Typical Shelf Life</b>	2 yrs
<b>VOC (As Supplied)</b>	357 g/lit
<b>Unit Size</b>	750 ml

## DRYING/OVERCOATING INFORMATION

	Drying			
	5°C	15°C	23°C	35°C
Touch Dry [ISO]	5hrs	4hrs	3hrs	2hrs
Dry To Walk On	4days	3days	2days	1days

  

	Overcoating Substrate Temperature							
	5°C		15°C		23°C		35°C	
Overcoated By	Min	Max	Min	Max	Min	Max	Min	Max
Interdeck	24hrs	4days	20hrs	3days	16hrs	2days	12hrs	1days

## APPLICATION AND USE

### Preparation

#### PREVIOUSLY PAINTED SURFACES:

**In Good Condition:** Wash down with Yacht Line Super Cleaner, rinse with fresh water and allow to dry. Abrade with 280-320 grade (grit) paper.

**In Poor Condition:** Remove all previous coatings and prime the substrate.

**PRIMING:** All preparation for bare substrates is covered on the appropriate primer datasheet.

**BARE WOOD:** Prime with Yacht Primer or UCP.

**STEEL:** Prime with Yacht Primer or Interprotect.

**ALUMINIUM:** Prime with Etch Primer followed by either Yacht Primer or Interprotect.

**GRP:** Wash down with Yacht Line Super Cleaner, rinse with fresh water and allow to dry.

Abrade with 180-220 grade paper. No priming necessary.

**AGED/WEATHERED GELCOATS:** Due to the potentially porous nature of aged/weathered gelcoats the risk of solvent/moisture entrapment after painting is much higher than when gelcoat is new. As a result this entrapment could lead to blistering of the paint film. To reduce the risk of paint film blistering it is recommended that 3 coats of Interprotect are applied to seal the gelcoat. Interprotect must be overcoated with Perfection Undercoat prior to topcoat application.

**ALL SUBSTRATES:** If any filling is required use the appropriate product from the Interfill range.

### Method

Sand the primer with 180-220 grade wet or dry paper. Remove dust with a dust wipe. Apply 1-2 coats.

### Hints

**Mixing** Stir well before use.

**Thinner** YTA800 Thinners No.1

**Cleaner** YTA800 Thinners No.1

**Ventilation and Humidity Control** Apply in dry, well ventilated conditions.

**Other** For best results either stipple by brush or use a mohair roller.

<b>Some Important Points</b>	Product temperature should be minimum 10°C and maximum 30°C. Ambient temperature should be minimum 5°C/40°F and maximum 35°C/95°F. Substrate temperature should be minimum 5°C/40°F and maximum 35°C/95°F.
<b>Compatibility/Substrates</b>	Suitable for all substrates and filled surfaces. Not suitable for permanently immersed surfaces. Do not clean with highly alkaline cleaners.
<b>Number of Coats</b>	1-2
<b>Coverage</b>	(Theoretical) - 9.50 (m <sup>2</sup> /lt)
<b>Recommended DFT</b>	50 microns dry
<b>Recommended WFT</b>	93 microns wet
<b>Application Methods</b>	Brush, Roller

## TRANSPORTATION, STORAGE AND SAFETY INFORMATION

**Storage** **GENERAL INFORMATION:**  
Exposure to air and extremes of temperature should be avoided. For the full shelf life of Interdeck to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/40°F and 35°C/95°F. Keep out of direct sunlight.  
**TRANSPORTATION:**  
Interdeck should be kept in securely closed containers during transport and storage.

**Safety** **GENERAL:** Read the label safety section for Health and Safety Information, also available from our Technical Help Line.  
**DISPOSAL:** Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.  
Remainders of Interdeck cannot be disposed of through the municipal waste route or dumped without permit. Disposal of remainders must be arranged for in consultation with the authorities.

**IMPORTANT NOTES** *The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal or injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.*  
**X** and International are registered trademarks of Akzo Nobel.

## Regional Addresses

**Head Office**  
International Paint Ltd  
P O Box 20980  
Oriol House  
16 Connaught Place  
London W2 2ZB  
United Kingdom  
tel: +44 (0) 171 479 6000  
fax: +44 (0) 171 479 6500

**European Region**  
International Paint Ltd  
Stoneygate Lane  
Felling, Gateshead  
Tyne & Wear NE10 0JY  
United Kingdom  
tel: +44 (0) 191 469 6111  
fax: +44 (0) 191 438 3977

**Asia Region**  
International Paint Singapore  
(Pte) Ltd  
449 Tagore Industrial Avenue  
01-03 Hong Joo Industrial  
Building  
Singapore 787820  
tel: +65 6453 1981  
fax: +65 6453 1778

**Australasia Region**  
International Paint  
115 Hyde Road  
Yeronga, Brisbane  
Queensland 4104  
Australia  
tel: +61 (0) 7 3892 8866  
fax: +61 (0) 7 3892 4287

**North America Region**  
International Paint Inc  
2270 Morris Avenue  
Union  
New Jersey 07083  
USA  
tel: +1 (0) 908 686 1300  
fax: +1 (0) 908 686 8545

**South America Region**  
International Paint  
Rod Rap tavares, KM 18.5  
Predio Administrativo 11  
Butanta CEP 05577-300  
Sao Paulo, Brazil  
tel: +55 (0) 11 3789 2000  
fax: +55 (0) 11 3789 2200



Ref: 05000108  
Issue Date: 14-Feb-2003  
Supersedes: 28-Nov-2002