



[www.RylardBoats.com](http://www.RylardBoats.com)

# Technical Data Sheet

**PRODUCT NAME:** **SILVOLINE ALUMINIUM PAINT**

---

**CODE NUMBER:** 03035

---

**PRODUCT DESCRIPTION:** Bright Aluminium decorative coating for use on all exposed deck ironwork; stantions; davits etc. Is also used as decorative finish in architectural applications, notably the lamp standards at Millennium Point, Birmingham.

---

**PERFORMANCE/USE:** Quick drying bright aluminium finish with excellent durability; weathering etc. Requires no special surface pre-treatment; can be applied directly to clean metals. However it is recommended that a full primer/undercoat process be used to ensure full corrosion protection.

---

**SURFACE PREPARATION:** It is recommended to apply Silvoline over fully prepared surfaces, the final undercoat being flatted with 320/360 wet & dry paper. Refer to our painting hints booklet before starting work.

---

**APPLICATION:** Apply by brush; roller; paint pad or spray. Use as supplied; do not thin. Minimum application temperature: 10°C

---

**DRYING/OVERCOATING:**

Touch/Dust dry(15°C)	30-40 minutes
Hard dry/Overcoating(15°C)	16-24 hours

---

**PHYSICAL PROPERTIES:**

Supply Viscosity	35-45 seconds/ISO 4 cup /23°C
Supply SG	0.98
Theoretical Coverage:	14 square metres per litre per coat
VOC Content:	457 grammes per litre
Flash Point / Class / UN No	≥32°C & ≤55°C / III / UN 1263
Pack Size	750 ml & 2.5 litre containers
Shelf Life	12 months unopened, stored at UK ambient temperatures.
Health & safety:	Refer to Product Safety Data Sheet before use.

*This information is given in good faith for the guidance of users, but is without warranty or liability. Any queries should be referred to our technical department,*

**Distributed by:**  
**Mainline**  
2 Sefton Road  
Litherland  
Liverpool L21 7PG  
Tel: 0151 920 6451  
Fax: 0151 920 6452

**Your Local Stockist:**