

WOOD

RECOMMENDED COATING SYSTEMS FOR NEW BOATS

ONE COMPONENT SYSTEM

BOTTOM		TOPSIDES	
SYSTEM N. 1 SYNTHETIC-CHLORINATED	SYSTEM N.2 EPOXY-CHLORINATED	SYSTEM N.3 CLEAR FINISH	SYSTEM N.4 ENAMEL FINISH
1 coat of CROMOMINIO-AT	1 coat of EPOSEALER (2-pack)	1-2 coats of POLIGLASS (2-pack, for complete sinking in the wood)	1 coat of CROMOMINIO-AT
3 coats of SOLVER PRIMER	2 coats of EPOFOND AM-9 (2-pack)	4 coats of TOPKAPI UV o STARWIND UV	1 coat of SINTOFILLER
2-3 coats of LONG LIFE or STANDARD or SELF-POLISH 2000 or SERENESSIMA or ALUFLIGHT	1 coat of SOLVER PRIMER	4 coats of STARWIND UV TOPKAPI UV o SUPERWIND	2 coats of SINTOFAST o SOTTOFONDO NAUTICA
	2-3 coats of LONG LIFE or STANDARD or SELF-POLISH 2000 or SERENESSIMA or ALUFLIGHT		2 coats of TOPKAPI GLOSS

TWO COMPONENT SYSTEM

TOPSIDES	
SYSTEM N.5 CLEAR FINISH	SYSTEM N.6 ENAMEL FINISH
2 coats of POLIGLASS	1 coat of EPOSEALER
2 coats of POLIGLASS o ACRIGLASS UV	2 coats of EPOFOND AM-9
2 coats of ACRIGLASS UV or SPACE CLEAR UV or POLISATIN or POLIMAT	1 coat of POLIFOND
	2 coats of ACRIGLASS ENAMEL or SPACE TOP or WHITEXT BUCCIATO

NOTE: The information is given to the best of our knowledge but since the conditions of use of our products are beyond our control, no warranty is given or to be implied in respect of such information. We are, at all times, willing to study customer's specific requirements involving our products in order to enable their most effective use. Drying times and the recommended thinning percentage are specified on the relevant product data sheets.

STEEL

RECOMMENDED COATING SYSTEMS FOR NEW BOATS

ONE COMPONENT SYSTEM

BOTTOM	TOPSIDES
SYSTEM N. 7 SINTHETIC-CHLORINATED	SYSTEM N.8 ENAMEL FINISH
2 coats CROMOMINIO-AT	2 coats of CROMOMINIO-AT
2 coats SOLVER PRIMER	2 coats of SOLVER PRIMER
2-3 coats LONG LIFE or STANDARD or SELF-POLISH 2000 or SERENESSIMA or ALUFLIGHT	2 coats of SINTOFAST or SOTTOFONDO NAUTICA
	2 coats of TOPKAPI GLOSS

TWO-COMPONENT SYSTEM

BOTTOM		TOPSIDE
SYSTEM N.9 BOTTOM	SYSTEM N.10 PROPELLERS,FLAPS, AND STERN DRIVES	SYSTEM N.11 ENAMEL FINISH
2 coats of EPOFOND AM-9	1 coat of ELIPRIMER	1 coat of EPOZINC 2C
2 coats of SOLVER PRIMER	2 coats of ELIFAX	1 coat of EPOFOND AM-9
2-3 coats of LONG LIFE or STANDARD or SELF-POLISH 2000 or SERENESSIMA or ALUFLIGHT		1 coat of EPOXY LIGHT FILLER
		1 coat of EPOFOND AM-9
		2 coats of POLIFOND
		2 coats of ACRIGLASS ENAMEL or SPACE TOP or WHITEXT BUCCIATO

NOTE: The information is given to the best of our knowledge but since the conditions of use of our products are beyond our control, no warranty is given or to be implied in respect of such information. We are, at all times, willing to study customer's specific requirements involving our products in order to enable their most effective use. Drying times and the recommended thinning percentage are specified on the relevant product data sheets.

ALUMINIUM AND LIGHT ALLOYS

RECOMMENDED COATING SYSTEMS FOR NEW BOATS

ONE COMPONENT SYSTEM

BOTTOM	TOPSIDES
SYSTEM N.12 EPOSSIDICO CLOROCAUCCIU'	SYSTEM N.13 GLOSS FINISH
2 coats of EPOFOND AM-9 (2-pack)	1 coat of EPOFOND AM-9 (2-pack)
2 coats of SOLVER PRIMER	2 coats of SINTOFAST
2-3 coats of SELF POLISH 2000 or ALUFLIGHT	2 coats of TOPKAPI GLOSS

TWO COMPONENT SYSTEM

TOPSIDES
CICLO N.14 ENAMEL FINISH
1 coat of EPOFOND AM-9
1 coat of EPOXY LIGHT FILLER
1 coat of EPOFOND AM-9
2 coats of POLIFOND
2 coats of ACRIGLASS ENAMEL or SPACE TOP or WHITEXT BUCCIATO

NOTE: The information is given to the best of our knowledge but since the conditions of use of our products are beyond our control, no warranty is given or to be implied in respect of such information. We are, at all times, willing to study customer's specific requirements involving our products in order to enable their most effective use. Drying times and the recommended thinning percentage are specified on the relevant product data sheets.

FIBREGLASS

RECOMMENDED COATING SYSTEMS FOR NEW BOATS

ONE COMPONENT SYSTEM

BOTTOM	TOPSIDES
SYSTEM N. 15 SYNTHETIC-CHLORINATED	SYSTEM N.16 ENAMEL FINISH
1 coat of UNIFIBER	1 coat of UNIFIBER
1 coat of SOLVER PRIMER	2 coats of SINTOFAST
2-3 coats of LONG LIFE or STANDARD or SELF POLISH 2000 or SERENESSIMA or ALUFLIGHT	2 coats of TOPKAPI GLOSS

TWO COMPONENT SYSTEM

BOTTOM		TOPSIDES	
SYSTEM N. 17 SYNTHETIC-CHLORINATED	SYSTEM N.18 ANTI-OSMOSI "PREVENTION TREATMENT"	SYSTEM N.19 ANTI-OSMOSI "CURING TREATMENT "	SYSTEM N.20 ENAMEL FINISH
1 coat of POLIFIBER	2 coats of EPOFOND AM-9 H.B.	2 coats of EPOSEALER	1 coat of POLIFIBER
1 coat of SOLVER PRIMER	1 coat of UNIFIBER	1 coat of EPOXY LIGHT FILLER	1 coat of EPOFOND AM-9
2-3 coats of LONG LIFE or STANDARD or SELF POLISH 2000 or SERENESSIMA or ALUFLIGHT	2-3 coats of LONG LIFE or STANDARD or SELF POLISH 2000 or SERENESSIMA or ALUFLIGHT	2 coats of EPOSEALER	2 coats of ACRIGLASS SMALTO or SPACE TOP or WHITEXT BUCCIATO
		1 coat of UNIFIBER	
		2-3 coats of LONG LIFE or STANDARD or SELF POLISH 2000 or SERENESSIMA or ALUFLIGHT	

NOTE: The information is given to the best of our knowledge but since the conditions of use of our products are beyond our control, no warranty is given or to be implied in respect of such information. We are, at all times, willing to study customer's specific requirements involving our products in order to enable their most effective use. Drying times and the recommended thinning percentage are specified on the relevant product data sheets.