

SABA, a strong bond

## Description

Deckfast MS is a one-component sealant for general use. Deckfast MS is very well suited for bonding teak decks on boards of yachts.

## Special properties

Excellent adherence to teakwood on ship decks and bonding zones of several materials.

Solvent based adhesives

- Long application time: approx. 60 minutes!!

- Continuous elastic

- No shrinkage

MSP sealants

- Resistant to sea water en aging

- Contains no solvents

Water based adhesives

## Method of use

For bonding teakwood ship decks: see system description SBS-2.

Clean and dry substrate. Apply with sealant gun (sausage) or air pump (Tin).

Silicone sealants

## Technical data

Foam coatings

Basis : Modified Silane Polymers

Consistence : pasty

Density : approx. 1310 kg/m<sup>3</sup>

Hotmelts

Solids content : approx. 100%

Skin time : approx. 60 minutes at 23 °C / 75% rh

Tack-free after : approx. 48 hours at 23°C / 75% rh

Epoxy products

Volume alteration : approx. 5% (DIN 52451)

Hardness Shore A : 35 (DIN 53505)

Module at 100% : 0.71 N/mm<sup>2</sup> (DIN 53504)

PU products

Tensile strength : 1.98 N/mm<sup>2</sup> (DIN 53504)

Elongation at break : approx. 426 % (DIN 53504)

Work temperature : > 5 °C

Polysulfide products

Storage temperature : minimum +5 °C, maximum +30 °C

Temperature resistance : approx. from -30 °C up to +80 °C

Primers

Shelf life Sausage : 15 months in unopened packing

Shelf life tin : 6 months in unopened packing

## Order information

Cleaning agents

Packing	sausage	tin
Content	600 ml	5 liter

Colour	black	black
Article no.	100829	100829

## Safety recommendations

See the corresponding material safety data sheet.



## SABA Dinxperlo BV

Industriestraat 3, NL-7091 DC Dinxperlo, Postbus 3, NL-7090 AA Dinxperlo, the Netherlands,  
Tel +31 (0)315 658999, Fax +31 (0)315 653207, E-mail info@saba.nl, Internet www.saba.nl

Our recommendations and instructions for use are based on the present status of know-how and technique. Clients and users should evaluate our products by themselves, with regard to utilization and requirements of their own choice. We shall take no responsibility in case our products are not being used subject to our recommendations and/or instructions for use. Furthermore, General Terms and Conditions of the Dutch Association "Nederlandse Vereniging van Rubber en Kunststoffabrikanten of November 1, 1992", will apply to our recommendations, instructions for use and the delivery of our products.

Version 2006/07