



# Seal One Fast

SABA, a strong bond

## Description

SABA Seal One Fast is a one component sealant on MS-Polymer basis. This sealant is a modification of the SABA Seal One HM sealant and can be sanded very fast. SABA Seal One Fast is especially suitable for sealing teak ship decks.

Solvent based adhesives

## Special properties

- To sand after 1 to 2 days (at 23°C / 75% rh)
- Excellent aging resistance
- No bubble formation during polymerisation
- Less formation of hollow joints

MSP sealants

## Method of use

Water based adhesives

Clean and degrease substrate. Treat the sides of the joints with SABA Primer Marine.

Silicone sealants

Apply separation tape to the bottom of the joints to prevent three-point adherence.

Foam coatings

Apply SABA Seal One Fast with hand gun or air pressure gun.

Detailed application instructions are given in system descriptions SBS -1 and SBS -5.

Hotmelts

## Technical data

Epoxy products

Basis	: silane modified polymers
Consistence	: pasty
Density	: approx. 1397 kg/m <sup>3</sup>
Solids content	: approx. 100%
Skin time	: approx. 15 minutes at 23 °C / 75% rh
Tack-free after	: approx. 24 hours at 23°C / 75% rh
Curing rate	: approx. 3 mm/24 hrs at 23 °C / 75% rh
Volume alteration	: < 5% (DIN 52451)
Maximum allowable movement	: approx 25%
Hardness Shore A	: approx. 38 (DIN 53505)
Module at 100%	: approx. 0.44 N/mm <sup>2</sup> (DIN 53504)
Tensile strength	: approx. 1.08 N/mm <sup>2</sup> (DIN 53504)
Elongation at break	: approx. 546 % (DIN 53504)
Work temperature	: minimum +5 °C, maximum 35°C
Storage temperature	: minimum +5 °C, maximum 25 °C
Temperature resistance	: from -30 °C up to +80 °C
Shelf life	: 15 months in unopened packing
Shelf life in tin	: 6 months in unopened packing

PU products

Polysulfide products

Primers

Cleaning agents

## Order information

Packing	cartridge	aluminium foil bag	tin
Content	290 ml	600 ml	17.5 litre

<b>Colour</b>	<b>black RAL 7021</b>
Article No.	100792

## Safety recommendations

See the corresponding material safety data sheet

### SABA Dinxperlo BV

Industriestraat 3, NL-7091 DC Dinxperlo, Postbus 3, NL-7090 AA Dinxperlo, the Netherlands, Tel +31 (0)315 658999, Fax +31 (0)315 653207, E-mail info@saba.nl, Internet www.saba.nl

Our recommendations and instructions for use are based on the present status of know-how and technique. Clients and users should evaluate our products by themselves, with regard to utilization and requirements of their own choice. We shall take no responsibility in case our products are not being used subject to our recommendations and/or instructions for use. Furthermore, General Terms and Conditions of the Dutch Association "Nederlandse Vereniging van Rubber en Kunststoffabrikanten of November 1, 1992", will apply to our recommendations, instructions for use and the delivery of our products.

Version number: 2006/07

