

## SEAJET SATIN VARNISH

SEAJET SATIN VARNISH provides a beautiful finish for all types of wood.

It has the following advantages:

- Scratch resistant one component interior varnish,
- Achieve a beautiful satin sheen on interior woodwork,
- Resistant to alcohol and most on board chemicals,
- Suitable for exterior use when applied over a full system of SEAJET UV VARNISH.

### TECHNICAL DATA

<b>Type</b>	One-component, traditional varnish.
<b>Recommended use</b>	Abrasion resistant satin varnish for interior and exterior use.

<b>Surface Preparation</b>	Existing varnish in good condition: Clean with SEAJET BOATWASH. Wash down with fresh water and let it dry. Flatten back with P280-P400 abrasive paper. Clean the surface with a tack rag. Surface in poor condition: Remove old varnish layers by sanding or stripping. Bare wood: Sand the surface with P80-P180 along the grain, followed by P280-P400. Remove all dust by thinner wiping and allow to completely dry. Application: Build up several coats of SEAJET UV VARNISH. Then apply SEAJET SATIN VARNISH on top. Thin upto 5% and apply two coats. Avoid painting varnish when windy, damp or in direct sunlight. Dry mornings are the best.
----------------------------	--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

<b>Physical Data</b>	Colour: Clear amber
	Flash point: 41 °C
	Volume solids %: 40 ± 2
	VOC (Theoretical): 450 g/l.

<b>Application Details</b>	Thinner: SEAJET Thinner U
	Application Data: Air spray, brush, roller
	Min. Temperature: 8 °C
	Max. humidity: 85% R.H.(Dew point + minimum 3°C)

<b>Spray Details</b>	Tip No.: 1,2-1,5 mm
	Paint output pressure: 2 - 3 bar
	Viscosity: 100 sec.(Ford Cup No.4)
	Thinning: 0 - 5 % (by brush) or 10-15 % by spray.

<b>Film thickness and spreading rate:</b>	Min.
	Film Thickness, wet: 75 μm
	Film Thickness, dry: 30 μm
	Spreading Rate: 13,3 m <sup>2</sup> /l (theoretical)

<b>Preferable preceding coating</b>	SEAJET UV VARNISH. Thin first coat for application on bare wood. Existing sanded varnish.
-------------------------------------	-------------------------------------------------------------------------------------------

<b>Preferable subsequent coating</b>	SEAJET SATIN VARNISH
--------------------------------------	----------------------

<b>Packing</b>	One Pack Product
----------------	------------------

<b>Notes</b>	-
--------------	---

**Coating data**

Temperature	Drying time (at DFT 30 $\mu$ )	Overcoating intervals (at DFT 30 $\mu$ )	Pot life	Dry to launch	Remarks
-5 °C	-	-	-	-	-
0 °C	-	-	-	-	-
5 °C	-	-	-	-	-
10 °C	-	-	-	-	-
20 °C	Surface dry:1 hour Hard dry:12 hours	Minimum: 12 hours Max.with itself: None	-	-	Wet or dry abrasive paper 320-400
30 °C	-	-	-	-	-

**Safety information:** If Health, Safety and Environmental information is required a Health and Safety Data Sheet can be obtained from Chugoku Paints B.V.

Personal Protection advice and additional information can be obtained from the product Health and Safety Data Sheet which is available on request. The minimum safety precautions in dealing with this paint are:

- Observe the precautionary notices displayed on the container.
- Provide adequate ventilation.
- Avoid skin contact and inhalation of spray mist.
- If the product comes into contact with the skin, wash thoroughly with luke warm water and soap or suitable cleaner. If the eyes are contaminated, irrigate with water and seek medical advice immediately.
- Since the product contains flammable materials, keep away from sparks and open flames. No smoking should be permitted in the area.

<b>Definitions:</b>		
Tolerances:		The numerical information quoted in this Technical Data Sheet is subject to normal manufacturing tolerances.
Spreading Rate:		The spreading rate can vary depending on application conditions, the geometrical complexity of the structure, the weather conditions, etc.
Volume Solids:		The volume solids figure given in this Technical Data Sheet is the percentage of dry film obtained from a given wet film thickness under specified application rate and conditions measured by the Chugoku Standard Method corresponding to ASTM method D2697.
Overcoating Intervals:		The intervals given assume preparation consistent with good painting
Hard dry:		The time taken until the product can be walked on without damaging it. Time taken until full mechanical strength is obtained is longer.
V.O.C.:		Theoretical quantity of volatile organic compounds in g/l.

**Disclaimer:** Data, specifications, directions and recommendations given in this data sheet represent test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use is not guaranteed and must be determined by user. Product data is subject to change without notice and automatically void two years from issue. All legal relations of Chugoku Paints B.V. will be governed by the Uniform Terms of Sale and Delivery of Chugoku Paints B.V. as last filed with the district court of Rotterdam and upon request they will be made available without charge. Chugoku Paints B.V. explicitly rejects the applicability of any General Conditions, which its contractual parties may use. Exclusive jurisdiction: competent Court in Rotterdam.

The Inspector will undertake to the best of their ability, to carry out assistance during application of the products delivered by Chugoku, by only rendering advice in connection with the application at site. The Inspector undertakes to carry out the project in a conscientious manner, but Chugoku and/or the Inspector will not accept any kind of liability, direct or indirect, if the project does not give the results expected. Under all circumstances, the Buyer remains responsible for the execution of the project. Any advice and/or assistance rendered by the Inspector will be subject to such (final) responsibility of the buyer, and moreover subject to the Uniform Terms of Sale and Delivery of Chugoku Paints B.V. Even when damages or delays have been caused by faults or negligence on the side of Chugoku and/or the Inspector, such will not result in any liability whatsoever of Chugoku or the Inspector. Liability of both Chugoku or the Inspector for any consequential damages is explicitly excluded.

Some products have been specially modified to adapt to specific European requirements with regard to European-, national- and local laws and regulations or with regards to specific European use requirements. As a result some physical properties in a TDS may differ from those given in the original Japanese TDS.