

SEAJET TEAK OIL

SEAJET TEAK OIL gives teak a new warmth.
For internal or external use on yachts.

TECHNICAL DATA

Type	One-component, teak oil.
Recommended use	Coating for wooden objects.

Surface Preparation

Treatment of new and untreated teak:

1. Sand the surface with P320 grade wet and dry sand paper to open the pores.
2. Clean the surface thoroughly with alcohol to remove all grease, old wax, etc. and sanding dust. Use a lint free cloth or one that doesn't shed.
3. When the surface is dry, apply the teak oil wet on wet with a damp (lint free) cloth, a sponge or a brush. You can apply up to 3 or 4 coats per hour. Then spread the oil to get an even coat.
4. When the surface has an even consistency, 20-35 minutes after the last application the treatment is finished. Remove excess oil with a lint free cloth.
5. If the surface appears a little patchy the next day, sand away excess oil with P320 abrasive paper, dipped in to the teak oil and wipe away sawdust with a lint free cloth. Apply one very thin coat of teak oil over the entire surface. This will give the surface an even appearance.

Physical Data	Colour: Clear
	Flash point: 37°C
	Volume solids %: 50 ± 2
	VOC (Theoretical): 405 g/l.

Application Details	Thinner: SEAJET THINNER U
	Application Data: Brush, roller
	Min. Temperature: 5 °C
	Max. humidity: 85% R.H. (Dew point + minimum 3°C)

Spray Details	Tip No.: Graco 721, 723
	Paint output pressure: 15.0 - 18.0 MPa
	Viscosity: 20 sec. (Ford Cup No.4)
	Thinning: 0 - 5% (by volume)

Film thickness and spreading rate:	Min.	Max.	
	Film Thickness, wet: 50	100	µm
	Film Thickness, dry: 25	50	µm
	Spreading Rate: 20,0	10,0	m ² /l (theoretical)

Preferable preceding coating	-
-------------------------------------	---

Preferable subsequent coating	SEAJET TEAK OIL
--------------------------------------	-----------------

Packing	One Pack Product
----------------	------------------

Notes	<p>Previously Treated Teak:</p> <ol style="list-style-type: none"> 1. Scrape and sand the wood until it looks like untreated teak. Then follow points 1-4 and maybe 5 as for untreated teak. 2. Teak which has been previously treated with polish, wax or similar should be cleaned with SEAJET THINNER A to remove contamination.
--------------	---

Coating data

Temperature	Drying time (at DFT 40 μ)	Overcoating intervals (at DFT 40 μ)	Pot life	Dry to launch	Remarks
-5 °C	-	-	-	-	-
0 °C	-	-	-	-	-
5 °C	-	-	-	-	-
10 °C	-	Minimum: 3 hours Max.with itself: None	-	-	-
20 °C	-	Minimum: 1,5 hours Max.with itself: None	-	-	-
30 °C	-	-	-	-	-

IMPORTANT:

Cloths etc., which have been used with teak oil should be burnt or washed in water due to danger of self-ignition.

Tools should be cleaned with SEAJET THINNER U.

Film thickness and spreading rate depends on application method.

Safety information: If Health, Safety and Environmental information is required a Health and Safety Data Sheet can be obtained from Chugoku Paints B.V.

Personal Protection advice and additional information can be obtained from the product Health and Safety Data Sheet which is available on request. The minimum safety precautions in dealing with this paint are:

- Observe the precautionary notices displayed on the container.
- Provide adequate ventilation.
- Avoid skin contact and inhalation of spray mist.
- If the product comes into contact with the skin, wash thoroughly with luke warm water and soap or suitable cleaner. If the eyes are contaminated, irrigate with water and seek medical advice immediately.
- Since the product contains flammable materials, keep away from sparks and open flames. No smoking should be permitted in the area.

Definitions:		
Tolerances:		The numerical information quoted in this Technical Data Sheet is subject to normal manufacturing tolerances.
Spreading Rate:		The spreading rate can vary depending on application conditions, the geometrical complexity of the structure, the weather conditions, etc.
Volume Solids:		The volume solids figure given in this Technical Data Sheet is the percentage of dry film obtained from a given wet film thickness under specified application rate and conditions measured by the Chugoku Standard Method corresponding to ASTM method D2697.
Overcoating Intervals:		The intervals given assume preparation consistent with good painting
Hard dry:		The time taken until the product can be walked on without damaging it. Time taken until full mechanical strength is obtained is longer.
V.O.C.:		Theoretical quantity of volatile organic compounds in g/l.

Disclaimer: Data, specifications, directions and recommendations given in this data sheet represent test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use is not guaranteed and must be determined by user. Product data is subject to change without notice and automatically void two years from issue. All legal relations of Chugoku Paints B.V. will be governed by the Uniform Terms of Sale and Delivery of Chugoku Paints B.V. as last filed with the district court of Rotterdam and upon request they will be made available without charge. Chugoku Paints B.V. explicitly rejects the applicability of any General Conditions, which its contractual parties may use. Exclusive jurisdiction: competent Court in Rotterdam.

The Inspector will undertake to the best of their ability, to carry out assistance during application of the products delivered by Chugoku, by only rendering advice in connection with the application at site. The Inspector undertakes to carry out the project in a conscientious manner, but Chugoku and/or the Inspector will not accept any kind of liability, direct or indirect, if the project does not give the results expected. Under all circumstances, the Buyer remains responsible for the execution of the project. Any advice and/or assistance rendered by the Inspector will be subject to such (final) responsibility of the buyer, and moreover subject to the Uniform Terms of Sale and Delivery of Chugoku Paints B.V. Even when damages or delays have been caused by faults or negligence on the side of Chugoku and/or the Inspector, such will not result in any liability whatsoever of Chugoku or the Inspector. Liability of both Chugoku or the Inspector for any consequential damages is explicitly excluded.

Some products have been specially modified to adapt to specific European requirements with regard to European-, national- and local laws and regulations or with regards to specific European use requirements. As a result some physical properties in a TDS may differ from those given in the original Japanese TDS.